

Item No. 104S
Removing Portland Cement Concrete

104S.1 Description

This item shall govern the demolition, removal and satisfactory disposal of existing Portland cement concrete, as classified, at locations indicated on the Drawings or as directed by the Engineer or designated representative.

This specification is applicable for projects or work involving either inch-pound or SI units. Within the text inch-pound units are given preference followed by SI units shown within parentheses.

104S.2 Submittals

The submittal requirements of this specification item may include:

- A. A permit when utility adjustments are made in the right-of-way, and
- B. A plan for removal and deposition of all 'broken up' existing Portland cement (p.c.) concrete materials and debris.

104S.3 Classification

Existing Portland cement concrete, when removed under this section, will be classified as follows:

- 1. Concrete Curb will include curb, curb and gutter and combinations thereof,
- 2. Concrete Slabs will include, but not be limited to, house slabs, patio slabs, porch slabs, concrete riprap and concrete pavement,
- 3. Sidewalks and Driveways will include concrete sidewalks and driveways,
- 4. Concrete Walls will include all walls, regardless of height, and wall footings,
- 5. Concrete Steps will include all steps and combinations of walls and steps,
- 6. Abandoned Foundations will include abandoned utility foundations,
- 7. Miscellaneous Concrete shall include all other concrete items, which are not identified in items 1 through 6 above.

104S.4 Materials

Mortar shall conform to mortar specified in Standard Specification Item No. 403S, "Concrete for Structures".

104S.5 Construction Methods

Prior to commencement of this work, all required erosion control and tree protection measures shall be in place. The existing utilities shall be located and protected as specified in the Standard Contract Documents, Section 00700, "General Conditions". A permit shall be required when utility adjustments are to be made in preparation for

highway construction, as specified in Section 5.2.0 of the City of Austin Utilities Criteria Manual.

The existing Portland cement concrete shall be broken up, removed in accordance with Item No. 101S, "Preparing Right of Way" and disposed of by the Contractor and deposited at a permitted disposal site.

When it is specified that only a portion of the existing Portland cement (p.c.) concrete is to be removed and that the remaining p.c. concrete will continue to serve its purpose, special care shall be exercised to avoid damage to that portion which will remain in place. Unless otherwise established by the Engineer or designated representative, existing p.c. concrete shall be cut to the neat lines, that are indicated on the Drawings, by sawing with an appropriate type circular concrete saw to a minimum depth of 1/2 inch (12.5 mm). Any reinforcing steel encountered shall be cut off 1 inch (25 mm) inside of p.c. concrete sawed line. Any existing p.c. concrete, which is damaged or destroyed beyond the neat lines so established, shall be replaced at the Contractor's expense. Remaining p.c. concrete shall be mortared to protect the reinforcing steel and provide a neat clean appearance.

When reinforcement is encountered during the removal of portions of existing structures to be modified, a minimum of 1 foot (300 mm) of steel length shall be cleaned of all old p.c. concrete and left in place to tie into the new construction where applicable. All unsuitable material shall be removed and replaced with approved material. All foundations, walls or other objectionable material shall be removed to a minimum depth of 18 inches (450 mm) below all structures and 12 inches (300 mm) below areas to be vegetated.

104S.6 Measurement

When included in the contract as a separate pay item, the removal of p.c. concrete curb and p.c. concrete wall as prescribed above will be measured by the lineal foot (meter: 1 meter is equal to 3.281 feet) in its original position regardless of the dimensions or size. The removal of p.c. concrete slabs, p.c. concrete sidewalks and driveways, as prescribed above, will be measured by the square foot (square meter: 1 square meter is equal to 10.764 square feet) in original position, regardless of the thickness and existence of reinforcing steel. Portland cement concrete steps removed will be measured per lineal foot (meter: 1 meter is equal to 3.281 feet) of each individual step tread including the bottom step. The removal of p.c. concrete foundations will be measured per each individual foundation. The removal of miscellaneous concrete will be measured ~~per~~ each per lump sum.

104S.7 Payment

The work and materials presented herein will generally not be paid for directly, but shall be included in the unit price bid for the item of construction in which this item is used.

When specified in the contract bid form as a separate pay item, the item will be paid for at the contract unit bid price(s) for "Remove P.C. Concrete Curb", "Remove P.C. Concrete Slab", "Remove P.C. Concrete Sidewalks and Driveways", "Remove P.C. Concrete Walls", "Remove P.C. Concrete Steps", "Remove P.C. Concrete Foundations" and "Remove Miscellaneous P.C. Concrete". The bid prices shall include full compensation for all Work herein specified, including the disposal of all material not

required in the Work, the furnishing of all materials, equipment, tools, labor and incidentals necessary to complete the Work.

Payment will be made under one of the following:

Pay Item No. 104S-A:	Remove P.C. Concrete Curb	Per Lineal foot.
Pay Item No. 104S-B:	Remove P.C. Concrete Slab	Per Square foot.
Pay Item No. 104S-C:	Remove P.C. Concrete Sidewalks and Driveways	Per Square foot
Pay Item No. 104S-D:	Remove P.C. Concrete Wall	Per Lineal foot.
Pay Item No. 104S-E:	Remove P.C. Concrete Steps	Per Lineal foot.
Pay Item No. 104S-F:	Remove P.C. Concrete Foundations	Per Each.
Pay Item No. 104S-G:	Remove Miscellaneous P.C. Concrete	Per Lump Sum.

End

<u>SPECIFIC</u> CROSS REFERENCE MATERIALS
Specification Item 104S, "REMOVING CONCRETE"

City of Austin Standard Contract Documents

<u>Designation</u>	<u>Description</u>
00700	General Conditions

City of Austin Utilities Criteria Manual

<u>Designation</u>	<u>Description</u>
Section 5.2.0	Permit for Excavation in the Public Right-of-Way

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 101S	Preparing Right of Way
Item No. 110S	Street Excavation
Item No. 111S	Excavation
Item No. 120S	Channel Excavation
Item No. 132S	Embankment
Item No. 403S	Concrete for Structures
Item No. 610S	Preservation of Trees and Other Vegetation

<u>RELATED</u> CROSS REFERENCE MATERIALS

City of Austin Standard Contract Documents

<u>Designation</u>	<u>Description</u>
01500	Temporary Facilities
01550	Public Safety and Convenience

The Code of the City of Austin, Code of Ordinances, Volume 1

<u>Designation</u>	<u>Description</u>
Article 14-11-181	Permit Required
Article 14-11-189	Conditions for Permit Issuance
Article 14-11-190	Excavation Sequence and Permit Term

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 201S	Subgrade Preparation
Item No. 602S	Sodding for Erosion Control
Item No. 604S	Seeding for Erosion Control

Item No. 622S Diversion Dike
 Item No. 628S Sediment Containment Dikes
 Item No. 642S Silt Fence

<u>RELATED CROSS REFERENCE MATERIALS - Continued</u>
Specification Item 104S, "REMOVING CONCRETE"

City of Austin Standard Details

<u>Designation</u>	<u>Description</u>
610S-1	Tree Protection Fence Locations
610S-2	Tree Protection Fence, Type B Chainlink
610S-3	Tree Protection Fence, Type B Wood
610S-4	Tree Protection Fence, Modified Type A
610S-5	Tree Protection Fence, Modified Type B
621S-1	Diversion
622S-1	Diversion Dike
624S-1	Earth Outlet Sediment Trap
625S-1	Grade Stabilization Structure
627S-1	Grass Lined Swale
627S-2	Grass Lined Swale With Stone Center
628S	Triangular Sediment Filter Dike
628S-1	Hay Bale Dike
629S-1	Brush Berm
630S-1	Interceptor Dike
631S-1	Interceptor Swale
632S-1	Storm Inlet Sediment Trap
633S-1	Landgrading
634S-1	Level Spreader
635S-1	Perimeter Dike
636S-1	Perimeter Swale
637S-1	Pipe Slope Drain (Flexible)
637S-2	Pipe Slope Drain (Flexible)
638S-1	Pipe Outlet Sediment Trap
639S-1	Rock Berm
641S-1	Stabilized Construction Entrance
642S-1	Silt Fence
643S-1	Stone Outlet Structure
644S-1	Stone Outlet Sediment Trap

Texas Department of Transportation: Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges

<u>Designation</u>	<u>Description</u>
Item No. 100	Preparing Right of Way
Item No. 104	Removing Concrete
Item No. 110	Excavation
Item No. 112	Subgrade Widening
Item No. 132	Embankment
Item No. 158	Specialized Excavation Work
Item No. 420	Concrete Structures

**Item No. 111S
Excavation**

111S.1 Description

This item shall govern: (1) the excavation and proper utilization or satisfactory disposal of all excavated materials, of whatever character, within the limits of the Work and (2) construction, compaction, shaping and finishing of all designated earthwork areas in accordance with the specification requirements outlined herein and in conformity with the required lines, grades and typical cross sections indicated on the Drawings or as directed by the Engineer or designated representative. When not otherwise included in the Contract Documents, this item shall include the work described in Specification Item Nos. 101S, "Preparing Right of Way", No. 102S, "Clearing and Grubbing", No. 104S, "Removing Portland Cement Concrete", No. 132S "Embankment" and No. 201S, "Subgrade Preparation".

This specification is applicable for projects or work involving either inch-pound or SI units. Within the text inch-pound units are given preference followed by SI units shown within parentheses.

111S.2 Submittals

The submittal requirements of this specification item may include:

- A. A permit when utility adjustments are made in the right-of-way,
- B. A plan for removal and deposition of all 'Waste' materials, and
- C. A Blasting Permit if blasting is required and allowed on the project.

111S.3 Classification

All excavation shall be unclassified and shall include all materials encountered regardless of their nature or the manner in which they are removed.

111S.4 Construction Methods

Prior to commencement of this work, all required erosion control and tree protection measures shall be in place. The existing utilities shall be located and shall be protected as specified in the Standard Contracts Document Section 00700, "General Conditions" and/or indicated on the Drawings. A permit shall be required when utility adjustments are to be made in preparation for construction in the right-of-way, as specified in Section 5.2.0 of the City of Austin Utilities Criteria Manual.

Construction equipment shall not be operated nor construction materials stockpiled under the canopies of trees, unless otherwise indicated on the Drawings. Excavation or embankment materials shall not be placed within the drip line of trees until tree wells are constructed, that conform to Specification Item No. 610S, "Preservation of Trees and Other Vegetation".

All excavation shall be performed as specified herein and shall conform to the established alignment, grades and cross sections indicated on the Drawings. Suitable excavated materials shall be utilized, insofar as practical, in constructing required embankments. The construction of all embankments shall conform to Specification Item No. 132S, "Embankment". No material shall be stockpiled within the banks of a waterway.

Unsuitable excavated materials or excavation in excess of that needed for construction shall be known as "Waste" and shall become the property of the Contractor. Unsuitable material encountered below the subgrade elevation in roadway cuts, when declared "Waste" by the Engineer or designated representative, shall be replaced with material from the roadway excavation or with other suitable material as approved by the Engineer. It shall become the Contractor's responsibility to dispose of this material off the limits of the right of way in an environmentally sound manner at a permitted disposal site.

All blasting shall conform to the Provisions of the Standard Contract Document Section 01550, "Public Safety and Convenience". In all cases, a Blasting Permit must be obtained in advance from the City of Austin, Department of Public Works and Transportation.

Adequate dewatering and drainage of excavation shall be maintained throughout the time required to complete the excavation work.

111S.5 Measurement

All accepted excavation will be measured by either Method A or B as follows:

(1) Method A

Measurement of the volume of excavation in cubic yards ~~(cubic meters: 1 cubic meter is equal to 1.308 cubic yards)~~ ~~(cubic meters: 1 square meter is equal to 1.196 square yards)~~ by the average end area methods. Cross-sectional areas shall be computed from the existing ground surface to the established line of the subgrade, as shown on typical sections in the Drawings, over the limits of the right of way or other work limits, including parkway slopes and sidewalk areas.

(2) Method B

Measurement of the volume of excavation in cubic yards ~~(cubic meters: 1 square meter is equal to 1.196 square yards)~~ ~~(cubic~~

meters: 1 cubic meter is equal to 1.308 cubic yards) based upon the average end area method taken from pre-construction cross sections and planned grades. The planned quantities for excavation will be used as the measurement for payment for this item.

111S.6 Payment

This item will be paid for at the contract unit bid price for "Excavation", as provided under measurement Method A or B as included in the bid. The bid price shall include full compensation for all work herein specified including dewatering, drainage, subgrade preparation, unless otherwise indicated, and the furnishing of all materials, equipment, tools, labor and incidentals necessary to complete the work.

Payment will be made under one of the following:

Pay Item No. 111S-A: Excavation Per Cubic Yard.
Pay Item No. 111S-B: Excavation, **Plan Quantity** Per Cubic Yard, **Plan Quantity**

End

<u>SPECIFIC</u> CROSS REFERENCE MATERIALS
Specification Item 111S, "EXCAVATION"

City of Austin Standard Contract Documents

<u>Designation</u>	<u>Description</u>
00700	General Conditions
01550	Public Safety and Convenience

City of Austin Utilities Criteria Manual

<u>Designation</u>	<u>Description</u>
Section 5.2.0	Permit for Excavation in the Public Right-of-Way

City of Austin Technical Specifications

<u>Designation</u>	<u>Description</u>
Item No. 101S	Preparing Right of Way
Item No. 102S	Clearing and Grubbing-
Item No. 104S	Removing Portland Cement Concrete
Item No. 132S	Embankment
Item No. 201S	Subgrade Preparation
Item No. 236S	Proof Rolling
Item No. 610S	Preservation of Trees and Other Vegetation

<u>RELATED</u> CROSS REFERENCE MATERIALS
Specification Item 111S, "EXCAVATION"

City of Austin Standard Contract Documents

<u>Designation</u>	<u>Description</u>
01500	Temporary Facilities

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 120S	Channel Excavation
Item No. 203	Lime Treatment for Materials In Place
Item No. 204S	Portland Cement Treatment for Materials In Place
Item No. 230S	Rolling (Flat Wheel)
Item No. 232S	Rolling (Pneumatic Tire)
Item No. 234S	Rolling (Tamping)
Item No. 602S	Sodding for Erosion Control
Item No. 604S	Seeding for Erosion Control
Item No. 622S	Diversion Dike
Item No. 628S	Sediment Containment Dikes
Item No. 642S	Silt Fence

City of Austin Standard Details

<u>Designation</u>	<u>Description</u>
No. 610S-1	Tree Protection Fence Locations
No. 610S-2	Tree Protection Fence, Type B Chainlink
No. 610S-3	Tree Protection Fence, Type B Wood
No. 610S-4	Tree Protection Fence, Modified Type A
No. 610S-5	Tree Protection Fence, Modified Type B
No. 621S-1	Diversion
No. 622S-1	Diversion Dike
No. 624S-1	Earth Outlet Sediment Trap
No. 625S-1	Grade Stabilization Structure
No. 627S-1	Grass Lined Swale
No. 627S-2	Grass Lined Swale With Stone Center
No. 628S	Triangular Sediment Filter Dike

RELATED CROSS REFERENCE MATERIALS - Continued

City of Austin Standard Details

<u>Designation</u>	<u>Description</u>
No. 628S-1	Hay Bale Dike
No. 629S-1	Brush Berm
No. 630S-1	Interceptor Dike
No. 631S-1	Interceptor Swale
No. 632S-1	Storm Inlet Sediment Trap
No. 633S-1	Landgrading
No. 634S-1	Level Spreader
No. 635S-1	Perimeter Dike
No. 636S-1	Perimeter Swale
No. 637S-1	Pipe Slope Drain (Flexible)
No. 637S-2	Pipe Slope Drain (Flexible)
No. 638S-1	Pipe Outlet Sediment Trap
No. 639S-1	Rock Berm
No. 641S-1	Stabilized Construction Entrance
No. 642S-1	Silt Fence
No. 643S-1	Stone Outlet Structure
No. 644S-1	Stone Outlet Sediment Trap

The Code of the City of Austin, Code of Ordinances, Volume 1

<u>Designation</u>	<u>Description</u>
Article 14-11-181	Permit Required

<u>Article 14-11-189</u>	<u>Conditions for Permit Issuance</u>
<u>Article 14-11-190</u>	<u>Excavation Sequence and Permit Term</u>
<u>Texas Department of Transportation: Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges</u>	
<u>Designation</u>	<u>Description</u>
Item No. 100	Preparing Right of Way
Item No. 110	Excavation
Item No. 112	Subgrade Widening
Item No. 132	Embankment
Item No. 150	Blading
Item No. 158	Specialized Excavation Work
Item No. 160	Furnishing and Placing Topsoil
Item No. 164	Seeding for Erosion Control
Item No. 204	Sprinkling
Item No. 210	Rolling (Flat Wheel)
Item No. 211	Rolling (Tamping)
Item No. 213	Rolling (Pneumatic Tire)
Item No. 260 Mixed)	Lime Treatment for Materials Used as Subgrade (Road
Item No. 265 Subgrade	Lime-Fly Ash (LFA) Treatment for Materials Used as
<u>Texas Department of Transportation: Manual of Testing Procedures</u>	
<u>Designation</u>	<u>Description</u>
Tex-103-E	Determination of Moisture Content of Soil Materials
Tex-104-E	Determination of Liquid Limit of Soils
Tex-105-E	Determination of Plastic Limit of Soils
Tex-106-E	Method of Calculating the Plasticity Index of Soils
Tex-114-E	Laboratory Compaction Characteristics and
Moisture- Soil	Density Relationship of Subgrade & Embankment
Tex-115-E of Soils	Field Method for Determination of In-Place Density and Base Materials

**Item No. 130S
Borrow**

130S.1 Description

This item shall govern required excavation, removal and proper utilization of materials secured from sources, selected by the Contractor and approved by the Engineer or designated representative. The compaction of embankments constructed from borrow as provided herein shall conform to the appropriate sections of Specification Item Nos. 132S, "Embankment" and 236S, "Proof Rolling".

Borrow will be used only when indicated on the Drawings or directed by the Engineer or designated representative and shall only be acquired from approved sources.

This specification is applicable for projects or work involving either inch-pound or SI units. Within the text inch-pound units are given preference followed by SI units shown within parentheses.

130S.2 Submittals

The submittal requirements of this specification item may include:

- A. Identification of Class, source and characteristics (P.I., linear shrinkage, etc.) of proposed borrow material, and
- B. A plan for managing and maintaining borrow sites.

130S.3 Materials

All authorized borrow shall conform to one of the following classes:

Class A (Select Borrow)

Class A Borrow material shall consist of suitable granular material, free from vegetation or other objectionable matter and reasonably free from lumps of earth. When tested by standard TxDOT laboratory methods Tex-105-E, Tex-106-E and Tex-107-E, the Class A Select Borrow, shall meet the following requirements:

The Liquid Limit shall not exceed	45
The Plasticity Index shall not exceed	15
The bar linear shrinkage shall not be less than	2

Class B (Borrow)

Class B Borrow material shall consist of suitable non swelling [i.e. soils with a plasticity index (P.I.) less than 20] earth material such as loam, clay or other such materials that will form a stable embankment.

Class C (Topsoil)

See Standard Specification Item No. 601S.3(A)

130S.4 Construction Methods

Prior to commencing this work, all required erosion control and environmental measures shall be in place. All suitable materials removed from excavations shall be used, insofar as practicable in the formation of embankments conforming to Specification Item No. 132S, "Embankment", as otherwise indicated on the Drawings or as directed by the Engineer or designated representative. The completed work shall conform to the established alignment, grades and cross section as shown on the Drawings. The additional material necessary to complete the work described above shall be "Borrow" of the class specified.

The Contractor shall arrange for borrow from one of the following sources:

1. Existing borrow pit,
2. New borrow pit, or
3. Surplus excavated material from a site, with a site development permit.

The Contractor shall notify the Engineer 3 weeks prior to opening a pit or any other borrow source to allow necessary testing for approval of materials. All borrow sites shall comply with the requirements of the site development permit.

During construction, borrow sources shall be kept drained to permit final cross sections to be measured, when required.

Borrow sites shall be managed and maintained to minimize the impact of the appearance of the natural topographic features and at no time create a potential hazard to the public.

130S.5 Measurement

Borrow will be measured by the cubic yard (cubic meters: 1 cubic meter is equal to 1.196 cubic yards) in its final position based upon the average end areas, calculated from pre-construction cross sections and plan grades. The plan quantities for Borrow or Topsoil will be used as the measurement for payment for this item.

130S.6 Payment

All work performed as required herein and measured as provided under "Measurement" will be paid for at the unit bid price. The bid prices shall include full compensation for furnishing all labor; all materials; all royalty and freight involved; all hauling and delivering on the road; and all tools, equipment and incidentals necessary to complete the work. Payment will not be made for unauthorized work.

Payment will be made under one of the following:

- | | | |
|-----------------------------|--|-----------------|
| Pay Item No. 130S-A: | Class A (Select Borrow), Plan Quantity | Per Cubic Yard. |
| Pay Item No. 130S-B: | Class B (Borrow), Plan Quantity | Per Cubic Yard. |
| Pay Item No. 130S-T: | Class C (Topsoil), Plan Quantity | Per Cubic Yard. |

End

<u>SPECIFIC</u> CROSS REFERENCE MATERIALS
Specification 130S, "BORROW"

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 132S	Embankment
Item No. 236S	Rolling (Proof)

Texas Department of Transportation: Manual of Testing Procedures

<u>Designation</u>	<u>Description</u>
Tex-105-E	Determination of Plastic Limit of Soils
Tex-106-E	Method of Calculating the Plasticity Index of Soils
Tex-107-E	Determination of Bar Linear Shrinkage of Soils

<u>RELATED</u> CROSS REFERENCE MATERIALS
Specification 130S, "BORROW"

City of Austin Standard Contract Documents

<u>Designation</u>	<u>Description</u>
00700	General Conditions

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 101S	Preparing Right of Way
Item No. 102S	Clearing and Grubbing
Item No. 110S	Street Excavation
Item No. 111S	Excavation
Item No. 230S	Rolling (Flat Wheel)
Item No. 232S	Rolling (Pneumatic Tire)
Item No. 234S	Rolling (Tamping)
Item No. 602S	Sodding for Erosion Control
Item No. 604S	Seeding for Erosion Control
Item No. 610S	Preservation of Trees and Other Vegetation
Item No. 622S	Diversion Dike
Item No. 628S	Sediment Containment Dikes
Item No. 642S	Silt Fence

City of Austin Standard Details

<u>Designation</u>	<u>Description</u>
No. 610S-1	Tree Protection Fence Locations
No. 610S-2	Tree Protection Fence, Type B Chainlink
No. 610S-3	Tree Protection Fence, Type B Wood
No. 610S-4	Tree Protection Fence, Modified Type A
No. 610S-5	Tree Protection Fence, Modified Type B
No. 621S-1	Diversion
No. 622S-1	Diversion Dike
No. 624S-1	Earth Outlet Sediment Trap
No. 625S-1	Grade Stabilization Structure
No. 626S-1	Grass Lined Swale
No. 627S-1	Grass Lined Swale With Stone Center
No. 628S	Triangular Sediment Filter Dike
No. 628S-1	Hay Bale Dike
No. 629S-1	Brush Berm
No. 630S-1	Interceptor Dike
No. 631S-1	Interceptor Swale
No. 632S-1	Storm Inlet Sediment Trap
No. 633S-1	Landgrading

No. 634S-1 Level Spreader

RELATED CROSS REFERENCE MATERIALS - Continued
Specification 130S, "BORROW"

City of Austin Standard Details

<u>Designation</u>	<u>Description</u>
No. 635S-1	Perimeter Dike
No. 636S-1	Perimeter Swale
No. 637S-1	Pipe Slope Drain (Flexible)
No. 637S-2	Pipe Slope Drain (Flexible)
No. 638S-1	Pipe Outlet Sediment Trap
No. 639S-1	Rock Berm
No. 641S-1	Stabilized Construction Entrance
No. 642S-1	Silt Fence
No. 643S-1	Stone Outlet Structure
No. 644S-1	Stone Outlet Sediment Trap

Texas Department of Transportation: Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges

<u>Designation</u>	<u>Description</u>
Item No. 100	Preparing Right of Way
Item No. 110	Excavation
Item No. 132	Embankment
Item No. 158	Specialized Excavation Work
Item No. 160	Furnishing and Placing Topsoil
Item No. 164	Seeding for Erosion Control
Item No. 204	Sprinkling
Item No. 210	Rolling (Flat Wheel)
Item No. 211	Rolling (Tamping)
Item No. 213	Rolling (Pneumatic Tire)

Texas Department of Transportation:
Manual of Testing Procedures

<u>Designation</u>	<u>Description</u>
Tex-103-E	Determination of Moisture Content of Soil Materials
Tex-104-E	Determination of Liquid Limit of Soils
Tex-114-E	Laboratory Compaction Characteristics and Moisture-Density Relationship of Subgrade & Embankment Soil
Tex-115-E	Field Method for Determination of In-Place Density of Soils and Base Materials

**Item No. 212S
Recycled Concrete Flexible Base**

212S.1 Description

This item governs furnishing and placing a crushed recycled concrete base course. "Recycled Concrete Flexible Base" shall be constructed on an approved, prepared surface in one or more courses conforming to the typical sections and to the lines and grades, indicated on the Drawings or established by the Engineer or designated representative.

This specification is applicable for projects or work involving either inch-pound or SI units. Within the text and accompanying tables, the inch-pound units are given preference followed by SI units shown within parentheses.

212S.2 Submittals

The submittal requirements of this specification item may include:

- A. Source, gradation and test results for the crushed recycled concrete material,
- B. Notification that the crushed recycled concrete stockpile is completed and ready for testing,
- C. Certification of compliance with TXDOT DMS 11000, "Evaluating and Using Non-hazardous Recyclable Material Guidelines", and
- D. Field density test results for in-place compacted flexible base,

212S.3 Material

A. Mineral Aggregate

The material shall be crushed recycled concrete meeting the requirements specified herein. The material shall be from sources approved by the City and shall consist of durable crushed recycled concrete that has been screened to the required gradation.

The recycled concrete material shall be free of reinforcing steel and other objectionable materials and shall have no more than 1.5% deleterious material (when tested in conformance with Tex-413-A) and 3000 ppm of soluble sulfates ASTM C1580).

Recycled concrete flexible base materials shall be tested according to the following TxDoT standard test methods:

a) Preparation for Soil Constants and Sieve Analysis	Tex-101-E
b) Liquid Limit ¹	Tex-104-E
c) Plastic Limit	Tex-105-E
d) Plasticity Index	Tex-106-E
e) Sieve Analysis	Tex-110-E
f) Wet Ball Mill ²	Tex-116-E

g) Triaxial Test	Tex-117-E, Part II
h) Deleterious Materials	Tex-413-A

1. Plasticity Index shall be determined in accordance with Tex-107-E (Linear Shrinkage) when liquid limit is unattainable as defined in Tex-104-E.
2. When a soundness value is required on the drawings, the material shall be tested in accordance with Tex-411-A.

The recycled concrete base material shall be stockpiled after crushing, then tested by the City's designated laboratory and approved by the Engineer or designated representative prior to being hauled to the Project.

The recycled concrete material shall be well graded and shall meet the following requirements. Additives such as but not limited to lime, cement or fly ash shall not be used to modify the aggregates to meet the requirements unless specified otherwise on the drawings.

Sieve Designation		Other Requirements	% Retained
US	SI		
1 3/4"	45 mm		0
7/8"	22.4 mm		10-35
3/8"	9.5 mm		30-50
#4	4.75 mm		45-65
#40	425 µm		70-85
		Maximum Plasticity Index	10
		Maximum Wet Ball Mill	42
Maximum Increase in passing #40 (425 µm) sieve from Wet Ball Mill Test			20

Minimum compressive strength when subjected to the triaxial test shall be 35 psi at 0 psi lateral pressure [240 kiloPascal (kPa) at 0 kPa lateral pressure] and 175 psi at 15 psi lateral pressure [1200 kiloPascal (kPa) at 100 kPa lateral pressure].

B. Asphaltic Material

Prime Coat. Prime Coat shall conform to the requirements of Standard Specification Item 306S, "Prime Coat", except for measurement and payment.

212S.4 Stockpiling, Storage and Management

A. Managing Material:

The stockpile shall be constructed on a relatively smooth area that has been cleared of debris, weeds, brush, trees and grass. Stockpiles shall contain between 25,000 and 50,000 cubic yards (19,100 to 38,200 cubic meters). The stockpile shall be constructed

using scrapers, bottom dumps or other similar equipment that allows dumping and spreading without rehandling. The stockpile shall be constructed to allow dumping and spreading in one direction only. The height of the stockpile shall not exceed the capabilities of available equipment to make a full cut (bottom to top) on any of the four sides.

A stockpile shall be completed before being tested by the City. The Contractor's supplier shall notify the City when a stockpile has been completed and is ready to be tested. The stockpile shall not be added to after it has been tested.

The Contractor shall provide material only from stockpiles that have been inspected, tested and accepted by the City. A ticket showing the date, source, stockpile number, and net weight (mass) shall be provided to the Inspector with each load of material delivered to the Project.

Because of its high absorptive properties, the recycled concrete material contained in a stockpile can potentially lose strength with subsequent moisture addition. As a consequence the City may require additional testing if an unprotected stockpile is exposed to significant extended rainfall or a stockpile remains open for an extended period of time.

Material shall be loaded from the stockpile by making successive vertical cuts through its entire depth.

B. Test Sampling:

The Contractor's supplier may choose the method of sample gathering for testing by the City's laboratory as follows:

1. The supplier shall make a full-height cut a sufficient distance into each side of the stockpile to obtain a uniform sample. The four samples (one from each side of the stockpile) shall then be combined and mixed into a single "test" specimen from which the City's laboratory can obtain a sample.
2. As the stockpile is constructed, a perpendicular cut will be made across the spreading direction at every two feet to four feet (0.6 to 1.2 meters) of height and the sample used to start a "mini" stockpile. The process shall be repeated in two feet to four feet (0.6 to 1.2 meter) increments of height, until the stockpile and the "mini" stockpile are completed. Samples shall be obtained from the "mini" stockpile in the same manner described in (1) above.

C. Testing and Acceptance:

When initial tests indicate that the material is unacceptable, the City may, if requested by the Contractor's supplier, sample and test the material one more time. The additional sampling and testing shall be paid for by the supplier.

212S.5 Construction Methods

A. Preparation of Subgrade:

Recycled concrete flexible base shall not be placed until the Contractor has verified by proof rolling that the subgrade has been prepared and compacted in conformity with

Standard Specification Item 201S, "Subgrade Preparation," to the typical sections, lines and grades indicated on the Drawings. Any deviation shall be corrected and proof rolled prior to placement of the flexible base material.

The Contractor shall not place recycled concrete flexible base until the subgrade has cured to the satisfaction of the Engineer or designated representative, regardless of whether or not the subgrade has been successfully proof rolled. As a minimum, this will be after the surface displays no damp spots and there is no evidence of "sponginess" in the subgrade.

B. First Lift:

Immediately before placing the recycled concrete flexible base material, the subgrade shall be checked for conformity with grade and section. The thickness of each lift of flexible base shall be equal increments of the total base depth. No single lift shall be more than six inches (150 mm) or less than three inches (75 mm) compacted thickness.

The material shall be delivered in approved vehicles. It shall be the responsibility of the Contractor to deliver the required amount of material. If it becomes evident that insufficient material was placed, additional material as necessary shall be delivered and the entire course scarified, mixed and compacted.

Material deposited upon the subgrade shall be spread and shaped the same day unless otherwise approved by the Engineer or designated representative. In the event inclement weather or other unforeseen circumstances render spreading of the material impractical, the material shall be spread as soon as conditions allow.

Additionally, if the material cannot be spread and worked the same day it is deposited, the Contractor shall "close up" the dump piles before leaving the job site. "Closed up" shall be defined as the use of a motor grader to blade all dump piles together, leaving no open space between piles.

The material shall be spread, sprinkled, if required, then thoroughly mixed; bladed, dragged and shaped to conform to the typical sections indicated on the Drawings.

All areas and "nests" of segregated coarse or fine material shall be corrected or removed and replaced with well-graded material.

Each lift shall be sprinkled as required to bring the material to optimum moisture content, and then compacted to the extent necessary to provide not less than the percent density specified in Section P212S.5.D, "Density." In addition to the requirements specified for density, the full depth of recycled concrete flexible base material shall be compacted to the extent necessary to remain firm and stable under construction equipment. After each section of recycled concrete flexible base material is completed, tests, as necessary, will be made by the Engineer or designated representative. As a minimum, three in-place density tests per section per day will be taken. If the material fails to meet the density requirements, it shall be reworked as necessary to meet these requirements. All initial density testing will be paid for by the City. All retesting shall be paid for by the Contractor.

Throughout the entire operation, the surface of the material shall be maintained by blading and, upon completion, shall be smooth and shall conform to the typical section indicated on the Drawings and to the established lines and grades.

In that area on which pavement is to be placed, any deviation in excess of 1/4 inch (6.5 mm) in cross section or 1/4 inch in a length of 16 feet (6.5 mm in a length of 5 meters) measured longitudinally shall be corrected by loosening, adding or removing material, and by reshaping and recompacting. All irregularities, depressions or weak spots shall be corrected immediately by scarifying the areas affected, adding suitable material as required, and by reshaping and recompacting. Should the lift, due to any reason or cause, lose the required stability, density and/or finish before the surfacing is complete, it shall be recompacted and refinished at the Contractor's expense.

C. Succeeding Lifts:

Construction methods for succeeding lifts shall be the same as prescribed for the first lift. For that lift of the recycled concrete flexible base upon which the curb and gutter will be constructed, as well as the last recycled concrete flexible base lift (i.e. top of the recycled concrete flexible base), the Contractor shall check the surface of the lift for conformity to the lines and grades by setting "blue tops" at intervals not exceeding 50 feet (15 meters) on the centerline, at quarter points, at curb lines or edge of pavement, and at other points that may be indicated on the Drawings.

When the thickness of a particular lift of the flexible base is in question, the Contractor shall check the surface of the lift for conformity to the lines and grades by setting "blue tops" at intervals not exceeding 50 feet (15 meters) on the centerline, at quarter points, at curb lines or edge of pavement, and at other points that may be indicated on the Drawings

D. Density:

The recycled concrete flexible base shall be compacted to not less than 100 percent density as determined by TxDOT Test Method Tex-113-E.

Field density determination shall be made in accordance with TxDOT Test Method Tex-115-E unless otherwise approved by the Engineer or designated representative. Each lift of the recycled concrete flexible base shall also be tested by proof rolling in conformity with Standard Specification Item 236S "Proof Rolling."

E. Priming:

Because of its high absorptive properties, the recycled concrete material can potentially lose strength if not protected from subsequent moisture addition. Consequently after the recycled concrete flexible base material has been compacted to not less than 100 percent density, and tested by proof rolling, a prime coat will be applied in accordance with Standard Specification Item 306S, "Prime Coat."

F. Curing:

Pavement materials, such as a tack coat or surface course, shall not be placed on the primed surface until the prime coat has been absorbed into the recycled concrete base course. At least 24 hours, or longer if designated by the Engineer or designated representative, shall be allowed when cutback asphalt is used as the prime coat.

212S.6 Measurement

"Recycled Concrete Flexible Base" will be measured by the cubic yard (~~cubic meters: 1 cubic meter is equal to 1.308 cubic yards~~)(~~cubic meter: 1 cubic meter equals 1.196 cubic yards~~), complete in place, as indicated in the Contract Documents.

212S.7 Payment

This item will be paid for at the contract unit bid price for "Recycled Concrete Flexible Base". The unit bid price shall include full compensation for all work specified herein, including the furnishing, hauling, placing and compacting of all materials; for rolling, proof rolling, recompacting and refinishing; for all water required; for retesting as necessary; for priming; and for all equipment, tools, labor and incidentals necessary to complete the Work.

Prime coat will not be measured for or paid for directly but shall be included in the unit price bid for Standard Specification Item P212S, "Recycled Concrete Flexible Base."

Payment will be made under one of the following:

Pay Item No. P212S-A: Recycled Concrete Flexible Base Per Cubic Yard.

END

SPECIFIC CROSS REFERENCE MATERIALS

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 201S	Subgrade Preparation
Item No. 236S	Proof Rolling
Item No. 306S	Prime Coat

Texas Department of Transportation: Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges

<u>Designation</u>	<u>Description</u>
Tex-101-E	Preparation of Soil and Flexible Base Materials for Testing
Tex-104-E	Determination of Liquid Limit of Soils
Tex-105-E	Determination of Plastic Limit of Soils
Tex-106-E	Method of Calculating the Plasticity Index of Soils
Tex-107-A	Determination of Bar Linear Shrinkage of Soils
Tex-110-E	Determination of Particle Size Analysis of Soils
Tex-113-E	Laboratory Compaction Characteristics and Moisture-Density Relationship of Base Materials and Cohesionless Sands
Tex-115-E	Field Method for Determination of In-Place Density of Soils and Base Materials
Tex-116-E	Ball Mill Method for Determination of the Disintegration of Flexible Base Material
Tex-117-E	Triaxial Compression Tests for Disturbed Soils and Base Materials

Tex-411-A	Soundness of Aggregate By Use Of Sodium Sulfate Or Magnesium Sulfate
Tex-413-A	Determination of Deleterious Material in Mineral Aggregate
Texas Department of Transportation: Departmental Material Specifications	
<u>Designation</u>	<u>Description</u>
DMS 11000	Guidelines for Evaluating and Using Nonhazardous Recyclable Materials (NRMs) in TxDOT Projects

American Society for Testing and Materials (ASTM)

<u>Designation</u>	<u>Description</u>
ASTM C-1580	Standard Test Method for Water-Soluble Sulfate in Soil

RELATED CROSS REFERENCE MATERIALS
--

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 210S	Flexible Base

City of Austin Standard Details

<u>Designation</u>	<u>Description</u>
No. 1000S-2	Flexible Base with Asphalt Surface Trench Repair-Existing Pavement
No. 510S-3	Typical Trench with Paved Surface
No. 1000S	Bus Stop Paving
No. 1000S-10	Local Street Sections
No. 1000S-11(1)	Residential and City of Austin Neighborhood Collector Street Sections
No. 1000S-11(2)	Industrial and Commercial Collector Street Sections
No. 1000S-12(1)	Primary Collector Street Sections
No. 1000S-12(2)	Primary Arterial Street Sections
No. 1000S-13(1)	Minor Arterial Street Sections (4 Lanes)
No. 1000S-13(2)	Minor Arterial Street Sections-(4 Lanes divided)
No. 1000S-14	Major Arterial Street Sections

City of Austin Utility Criteria Manual

<u>Designation</u>	<u>Description</u>
Section 5.8.2	Flexible Base
Section 5.7.3	Flexible Base with Asphalt Surface
Section 5.9.1	Excavation in Alley

City of Austin Transportation Criteria Manual

<u>Designation</u>	<u>Description</u>
Section 3.2.0	General Criteria
Section 3.4.3 .D	Layer Data-Minimum Thickness
Table 3-1	Minimum Layer Thickness
Section 3.4.3 .F	Layer Data- Minimum Thickness
Table 3-2	Layer Thickness Increment
Section 3.4.3 .J	Layer Data- Stiffness Coefficient
Table 3-3	Stiffness Coefficient
Table 3-9	Recommended Salvage values
Table 3-10	AASHTO Layer Coefficients

Item No.320S
Two Course Surface Treatment

320S.1 Description

This item shall govern the construction of a wearing surface composed of a double application of asphaltic material, each covered with aggregate, constructed on existing pavements, a prepared base course or surface in accordance with these specifications.

This specification is applicable for projects or work involving either inch-pound or SI units. Within the text, the inch-pound units are given preference followed by SI units shown within parentheses.

320S.2 Submittals

The submittal requirements of this specification item include:

- A. Recommended design mix (asphaltic material, aggregate type, modifier type and %)
- B. Test results on the asphaltic material (Viscosity, penetration, solubility, ductility, stability, distillation test, residue tests, etc.).
- C. Test results on the aggregate (gradation and percent wear).
- D. Characteristics (i.e. manufacturer, rate of application, speed, etc.) of the proposed distributor and aggregate spreader.
- E. List of facilities and equipment proposed for temperature measurements.
- F. List of facilities and equipment proposed for storage and handling of asphaltic materials.

320S.3 Materials

All material shall be of the type(s) and grade(s) shown on the Drawings and shall conform to the pertinent material requirements for the following items:

A. Asphaltic Materials

The asphaltic materials used shall conform to Item No. 301S, "Asphalts, Oils and Emulsions" as follows:

- 1. Air Temperature 65 to 80⁰ F (18 to 27⁰C), HFRS-2
- 2. Air Temperature over 81⁰F (27⁰C), RS-2

B. Aggregate

The aggregate materials shall conform to Item No. 302S, "Aggregate for Surface Treatments" as follows:

1. First Course

Grade 3

2. Second Course

Grade 5

C. Aggregate (Stockpiled)

When the Drawings include the Item, "Aggregate (Stockpiled)", aggregate of the type and grade specified for the surface treatment shall be stockpiled within the limits of the project at sites designated on the drawings or as directed by the Engineer or designated representative. Stockpile sites shall be leveled, if required and prepared as specified herein. The Contractor shall load, haul, distribute and apply the stockpiled aggregate in accordance with specification requirements governing for this item. The stockpile areas and remaining stockpiles shall be left in a neat condition satisfactory to the Engineer or designated representative.

D. Temporary Pavement Markings

Temporary pavement markings shall conform to Item No. 864S, "Abbreviated Pavement Markings".

320S.4 Construction Methods

Prior to commencement of this work, all required erosion control and tree protection measures shall be in place and the utilities located and protected as specified in the City of Austin Standard Contract Documents, Section 00700, "General Conditions". Construction equipment shall not be operated within the drip line of trees unless otherwise indicated. Construction materials shall not be stockpiled under the canopies of trees. Excavation or embankment materials shall not be placed within the drip line of trees until tree wells are constructed.

The two course surface treatment shall be applied when the air temperature is above 50°F (10°C) and rising. Air temperature shall be taken in the shade and away from artificial heat. The two course surface treatment shall not be applied when the temperature of the roadway surface is below 60°F (16°C).

When latex modified asphalt cement is specified, the two course surface treatment shall be applied when the air temperature is above 70°F (21°C) and rising. Air temperature shall be taken in the shade and away from artificial heat. The two course surface

treatment shall not be applied when the temperature of the roadway surface is below 70°F(21°C).

Asphaltic material shall not be placed when general weather conditions, in the opinion of the Engineer or designated representative, are not suitable.

The area to be treated shall be cleaned of dirt, dust or other deleterious matter by sweeping or other approved methods. If deemed necessary by the Engineer or designated representative, the surface shall be lightly sprinkled just prior to the first application of asphaltic material.

The Contractor shall be responsible for the proper preparation of all stockpile areas before aggregates are placed thereon, including leveling, cleaning of debris necessary for protection of the aggregate to prevent any contamination thereof and clean up of any stockpile area at the completion of the work.

All storage tanks, piping, retorts, booster tanks and distributors used in storing or handling asphaltic materials shall be kept clean and in good operating condition at all times and shall be operated in such manner that there will be no contamination of the asphaltic material with foreign material. It shall be the responsibility of the Contractor to provide and maintain in good working order a recording thermometer at the storage heating unit at all times.

Application temperatures will be determined by weather conditions within the limits recommended in Specification Item 301S, "Asphalts, Oils and Emulsions", as determined by the Engineer or designated representative.

The Contractor shall provide all necessary facilities for determining the temperature of the asphaltic material in all of the heating equipment and in the distributor for determining the rate at which it is applied and for securing uniformity at the junction of two distributor loads. The distributor shall have been calibrated within three (3) years from the date it is first used on this project. The Contractor shall furnish the Engineer or designated representative with an accurate and satisfactory record of such calibration. After beginning the work, should the rate of the asphaltic material appear to be inappropriate, the distributor shall be adjusted to provide a satisfactory rate before proceeding with the work.

When a uniform application of asphaltic material is not being achieved, the Engineer or designated representative may require that the Contractor provide an operator at the rear of the distributor to manually control the spray bar operations.

Asphaltic material for each course may be applied for the full width of the surface treatment in one application, unless the width exceeds 26 feet (8 meters). No traffic or hauling will be permitted over the freshly applied asphaltic material. The asphaltic material shall not be applied until immediate covering is assured.

A. First Course

Asphaltic material for the first course shall be applied on the clean surface by an approved type of self-propelled pressure distributor so operated as to distribute the material, evenly and smoothly, under a pressure necessary for proper distribution at a rate of 0.30 to 0.35 gallons per square yard (1.4 to 1.6 liters per square meter) or as directed by the Engineer or designated representative.

Aggregate for the first course shall be immediately and uniformly applied and spread by an approved self-propelled continuous feed aggregate spreader, unless otherwise indicated or authorized by the Engineer in writing. The aggregate shall be applied at the approximate rate of 15 to 20 lbs. per square yard (8 to 11 kilograms per square meter) or as directed by the Engineer or designated representative. The Contractor shall be responsible for the maintenance of the surface of the first course until the second course is applied.

The entire surface shall then be broomed, bladed or raked as required by the Engineer and shall be thoroughly rolled in accordance with Specification Item 230S, "Rolling (Flat Wheel)" with power rollers of the three-wheel or tandem, self-propelled type, weighing not less than 3 tons (2.7 megagrams) nor more than 6 tons (5.4 megagrams). All wheels shall be flat.

In lieu of the rolling equipment specified, the Contractor may, upon written permission from the Engineer or designated representative, operate other compacting equipment that will produce equivalent relative compaction in the same period of time as the specified equipment. If the substituted compaction equipment fails to produce the desired compaction within the same period of time as would be expected of the specified equipment, as determined by the Engineer or designated representative, its use shall be discontinued. Rollers shall be maintained in good repair and condition and shall be approved by the Engineer or designated representative prior to their use.

B. Second Course

It is the intent of this specification that the application of asphalt and aggregate for the second course be applied within the same day or immediately thereafter and prior to opening the roadway to traffic.

The second course shall consist of asphaltic material and aggregate applied and covered in the manner specified for the first application. The surface shall then be broomed, bladed or raked as required by the Engineer or designated representative and thoroughly rolled in accordance with Standard Specification Item 232S, "Rolling (Pneumatic Tire)" with a pneumatic tire roller. Asphaltic materials for the course shall be applied at the rate of 0.25 gallons per square yard (1.1 liters per square meter) or as directed by the Engineer or designated representative. Aggregate for the second course shall be applied at the rate of 14 to 18 lbs. per square yard (7.5 to 10 kilograms per square meter) or as directed by the Engineer or designated representative.

The Contractor shall be responsible for the maintenance of the surface treatment until the work is accepted by the Engineer or designated representative. All holes or failures in the surface shall be repaired by use of additional asphalt and aggregate. All fat or bleeding surfaces shall be covered with approved cover material in such a manner that the asphaltic material will not adhere to or be picked up by the wheels of vehicles.

Temporary pavement markings shall be placed in accordance with Item No. 864S, "Abbreviated Pavement Markings".

320S.5 Measurement

A "Two Course Surface Treatment" application shall be measured by the square yard (square meter: 1 square meter equals 1.196 square yards) of completed and accepted two-course surface treatment.

320S.6 Payment

The work performed and materials furnished as prescribed by this item and measured as provided under "Measurement" will be paid at the unit bid price for two course surface treatment. The price shall each include full compensation for: a) cleaning and sprinkling the base; furnishing, preparing, hauling and placing all materials, and rolling, b) all freight involved; c) all manipulations, labor, tools, equipment cleanup, and temporary pavement markings and d) all incidentals necessary to complete the work.

Payment will be made under the following:

Pay Item No. 20S-A:	Two Course Surface Treatment	Per Square Yard, Plan
	<u>Plan Quantity</u>	<u>Quantity</u>

End

SPECIFIC CROSS REFERENCE MATERIALS

Specification Item 320S "Two Course Surface Treatment"

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 232S	Rolling (Pneumatic Tire)
Item No. 301S	Asphalts, Oils and Emulsions
Item No. 302S	Aggregates for Surface Treatments
Item No. 642S	Silt Fence (SF)
Item No. 864S	Abbreviated Pavement Markings

RELATED CROSS REFERENCE MATERIALSCity of Austin Standard Contract Documents

<u>Designation</u>	<u>Description</u>
Section 00700	General Conditions

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 206S	Asphalt Stabilized Base
Item No. 210S	Flexible Base
Item No. 306S	Prime Coat
Item No. 307S	Tack Coat
Item No. 310S	Emulsified Asphalt Treatment
Item No. 311S	Emulsified Asphalt Repaving
Item No. 312S	Seal Coat
Item No. 340S	Hot Mix Asphaltic Concrete Pavement
Item No. 341S	Paving Fabric
Item No. 350S	Heating, Scarifying and Repaving
Item No. 351S	Recycling Agent

City of Austin Standard Details

<u>Designation</u>	<u>Description</u>
1000S-10	Local Street Sections
1000S-11(1)	Residential and Neighborhood collector Street Sections
1000S-11(2)	Industrial and Collector Street Sections
1000S-12(1)	Primary Collector Street Sections
1000S-12(2)	Primary Arterial Street Sections
1000S-13(1)	Minor Arterial Street Sections (4 Lanes)
1000S-13(2)	Minor Arterial Street Sections- (4 Lanes divided)
1000S-14	Major Arterial Street

Texas Department of Transportation: Standard Specifications for Construction And Maintenance of Highways, Streets, and Bridges

<u>Designation</u>	<u>Description</u>
Item 300	Asphalts, Oils and Emulsions
Item 301	Asphalt Antistripping Agents
Item 310	Prime Coat (Cutback Asphaltic Materials)
Item 314	Emulsified Asphalt Treatment
Item 316	Surface Treatments
Item 345	Asphalt Stabilized Base (Plant Mixed)
Item 354	Planing and/or Texturing Pavement

Item No. 340S
Hot Mix Asphaltic Concrete Pavement**340S.1 Description**

This item shall govern base, level up, and pavement surface courses composed of a compacted mixture of aggregate and asphaltic cement mixed hot in a mixing plant. The hot mix asphaltic (HMA) concrete pavement shall be constructed on a previously completed and approved subgrade, subbase material, base material, concrete slab or existing pavement.

This specification is applicable for projects or work involving either inch-pound or SI units. Within the text and accompanying tables, the inch-pound units are given preference followed by SI units shown within parentheses.

340S.2 Submittals

The submittal requirements of this specification item may include:

- A. A mix design submittal including the plant corrected Job Mix Formula (JMF) for the hot mix asphaltic concrete,
- B. Certification that the aggregate materials meet appropriate quality requirements.
- C. Particle-size gradation and specific gravity tests on all aggregate materials.
- D. Certification that the asphalt cement for paving materials meet appropriate quality requirements.

340S.3 Materials

The Contractor shall furnish materials to meet the requirements specified herein and shall be solely responsible for the quality and consistency of the product delivered to the Project.

- A. Aggregate: The aggregate shall be composed of coarse aggregate, a fine aggregate and, if required or allowed, mineral filler and reclaimed asphalt pavement (RAP). RAP use will be allowed in all base course mixtures except as specifically excluded herein, in the Contract Documents or on the Drawings, provided no more than 20% RAP is used.

RAP use will not be permitted in pavement surface courses.

Aggregates shall meet the quality requirements of Table 1 and other requirements as specified herein. The aggregate contained in RAP will not be required to meet Table 1 requirements unless indicated otherwise on the Drawings.

1. Coarse Aggregate: Coarse aggregate is defined as that part of the aggregate retained on the No. 10 (2.00 mm) sieve and shall consist of clean, tough, durable fragments of crushed stone or crushed gravel of uniform quality throughout.

Gravel from each source shall be crushed to the extent that it has a minimum of 85% of the particles retained on the No. 4 (4.75 mm) sieve with two or more mechanically induced crushed faces as determined by TxDOT Test Method TEX-460-A (Part I). The material passing the No. 4 (4.75 mm) sieve and retained on the No. 10 (2.00 mm) sieve must be the produced from crushing aggregate that was originally retained on the No. 4 (4.75 mm) sieve.
2. Reclaimed Asphalt Pavement (RAP): RAP is defined as a salvaged, milled, pulverized, broken or crushed asphaltic pavement. The RAP to be used in the mix shall be crushed or broken to the extent that 100 percent will pass the 2-inch (50 mm) sieve.

The RAP shall be stockpiled in such a manner that assures that it will not become contaminated by dirt or other objectionable materials. Unless indicated otherwise on the Drawings, stockpiled, crushed RAP must not exhibit a decantation more than 5 percent or a plasticity index more than 8, when tested in accordance with TxDOT Test Method Tex-406-A, Part I, or Test Method Tex-106-E, respectively.

- 3. Fine Aggregate: Fine aggregate is defined as that part of the aggregate passing the No. 10 (2.00 mm) sieve and shall be of uniform quality throughout. A maximum of 15 percent of the total aggregate may be field sand or other uncrushed fine aggregate.

Screenings shall be supplied from sources whose coarse aggregate meets the abrasion and magnesium sulfate soundness loss requirements shown in Table 1.

- a) Unless indicated otherwise on the Drawings, stone screenings, which are the product of a rock crushing operation, are required and shall meet the following gradation requirements when tested in accordance with TxDOT Test Method Tex-200-F, Part I.

Material	Percent by Weight (Mass)
Passing 3/8 inch (9.50 mm) sieve.....	100
Passing No. 10 (2.00 mm) sieve.....	70-100
Passing No. 200 (75 µm) sieve.....	0-15

- b) Crushed gravel screenings may be used with, or in lieu of, stone screenings only when indicated on the Drawings. Crushed gravel screenings must be the product of crushing aggregate that was originally retained on the No. 4 (4.75 mm) sieve and must meet the gradation for stone screenings shown above.
- 4) Mineral Filler: Mineral filler shall consist of thoroughly dried stone dust, Portland cement, fly ash, lime or other mineral dust approved by the Engineer or designated representative. The mineral filler shall be free from foreign matter.

Portland cement manufactured in a cement kiln fueled by hazardous waste shall be considered as an approved product if the production facility is authorized to operate under regulation of the Texas Natural Resource Conservation Commission (TNRCC) and the U. S. Environmental Protection Agency (EPA). Supplier shall provide current TNRCC and EPA authorizations to operate the facility.

Fly ash obtained from a source using a process fueled by hazardous waste shall be considered as an approved product if the production facility is authorized to operate under regulation of the Texas Natural Resource Conservation Commission (TNRCC) and the U. S. Environmental Protection Agency (EPA). Supplier shall provide current TNRCC and EPA authorizations to operate the facility.

The addition of baghouse fines or other collected fines will be permitted if the mixture quality is not adversely affected in the opinion of the Engineer or designated representative. In no case shall the amount of material passing the No. 200 (75 µm) sieve exceed the tolerances of the job-mix formula or the master gradation limits.

When tested by TEX-200-F (Part I or Part III, as applicable), the mineral filler shall meet the following gradation requirements. Baghouse fines are not required to meet the gradation requirements.

Material	Percent by Weight (mass)
Passing No. 30 (600 µm) Sieve.....	95 - 100
Passing No. 80 (187.5 µm) Sieve, not less than.....	75
Passing No. 200 (75 µm) Sieve, not less than.....	55

TABLE 1: AGGREGATE QUALITY REQUIREMENTS *

Requirement	Test Method	Amount
COARSE AGGREGATE		
Deleterious Material, percent, maximum	Tex-217-F, I	1.5
Decantation, percent, maximum	Tex-217-F, II	1.5
Los Angeles Abrasion, percent, maximum	Tex-410-A	40
Magnesium Sulfate Soundness Loss 5 cycle, percent, maximum	Tex-410-A	30
FINE AGGREGATE		
Linear Shrinkage, maximum	Tex-107-E, II	3
COMBINED AGGREGATES		
Sand Equivalent Value, minimum	Tex-203-F	45

* - Aggregates, without added mineral filler or additives, combined as used in the job-mix formula (Plant Corrected).

B. Asphaltic Material

1. Paving Mixture. Asphalt cement for the paving mixture shall conform to the requirements of Standard Specification Item No. 301S, "Asphalts, Oils and Emulsions", for AC-20 or PG64-22, Styrene (SBS) Modified Asphalt Cement, AC-SBS Blend AC-45P or PG76-22S, unless otherwise indicated in the Project Documents.
2. Tack Coat: Tack Coat shall conform to Standard Specification Item No. 307S, "Tack Coat".

- C. Additives: Additives to facilitate mixing and/or improve the quality of the asphaltic mixture or tack coat may be used with the authorization of the Engineer or designated representative. The Contractor may choose to use either lime or a liquid anti-stripping agent to reduce moisture susceptibility of the aggregate.

340S.4 Paving Mixtures

An asphalt mixture design is developed by a laboratory process, which includes the determination of the quality and quantity of the asphalt cement and the individual aggregates, and the testing of the combined mixture (Laboratory Design). The Laboratory Design is subsequently revised to produce an appropriate job mix formula.

The job mix formula (JMF) lists the quantity of each component to be used in the mix after the laboratory design has been adjusted by running it through a particular plant (i.e. the mix design is Plant Corrected). The JMF will be the standard to which the Acceptance Plan will be applied. The JMF of one drum or batching unit shall not be used for another unit.

The Contractor shall submit to the Engineer on forms provided by the Engineer or designated representative, an asphalt mixture design reviewed, signed and sealed by a Registered

Professional Engineer licensed in the State of Texas or certified by a TxDOT Level II Certified Asphalt Technician. An asphalt mixture design shall be submitted for a comprehensive review every two (2) years. Mix designs older than one year will not be accepted without a review of current test data of the proposed materials and current mix design to ensure that the materials meet specification requirements.

The JMF (Plant Corrected) shall be submitted to the Engineer or designated representative on a form provided by the Engineer through the Construction Inspector or Project Manager of the Project for review, for each individual Project, a minimum of three (3) working days before the mixture is to be placed. Under no circumstances will a mixture be placed before its use is reviewed and approved by the Engineer or designated representative.

Performance of the mix design shall remain the responsibility of the Contractor.

- A. Mixture Design: The mix shall be designed in accordance with TxDOT Construction Bulletin C-14 and Test Method Tex-204-F to conform with the requirements herein. The master grading limits of the appropriate type and the JMF will be plotted on a graduated chart with sieve sizes raised to the 0.45 power and will be submitted to the Engineer or designated representative with the asphalt mixture design.

The Bulk Specific Gravity of aggregates in RAP will be determined on extracted aggregates.

- B. Types: The blend of coarse aggregate, fine aggregate, and mineral filler, if allowed, that is established by TxDOT Test Method Tex-200-F, Dry Sieve Analysis, shall conform to the master gradation shown in Table 2 for the type of specified mixture. The voids in the mineral aggregate (VMA) will be determined as a mixture design requirement only, in accordance with TxDOT Test Method Tex-207-F, and shall not be less than the value indicated in Table 2.

TABLE 2: Master Grading - Percent Passing by Weight (Mass) or Volume

Sieve Size US (SI)	Type A Coarse Base	Type B Fine Base	Type C Coarse Surface	Type D Fine Surface	Type F Fine Mixture
1-1/2" (37.5 mm)	100				
1-1/4" (31 mm)	95-100				
1" (25 mm)		100			
7/8" (22 mm)	70-90	95-100	100		
5/8" (15.5 mm)		75-95	95-100		
1/2" (12.5 mm)	50-70			100	
3/8" (9.5 mm)		60-80	70-85	85-100	100
1/4" (6.25 mm)					95-100
No. 4 (4.75 mm)	30-50	40-60	43-63	50-70	
No. 10 (2.00 mm)	20-34	27-40	30-40	32-42	32-42
No. 40 (425 µm)	5-20	10-25	10-25	11-26	9-24
No. 80 (187.5 µm)	2-12	3-13	3-13	4-14	3-13
No. 200 (75 µm)	1-6*	1-6*	1-6*	1-6*	1-6*
VMA % minimum	11	12	13	14	15
Rec. Min. Lift	3" (75 mm)	2" (50 mm)	1-3/4" (45 mm)	1" (25 mm)	3/4" (20 mm)

- C. Tolerances: Fluctuations in the aggregate gradation and asphalt content of the Job Mix Formula (JMF) shall not vary by more than the following criteria but the aggregate gradation shall be limited to the range of the master gradation as established by TEX-210-F.

SIEVES	Percent By Weight (Mass)
2" (50 mm) Sieve through No. 10 (2.00 mm) Sieve	±5.0
No. 40 (425 µm) through No. 200 (75 µm) Sieve	± 3.0
Asphalt Content	±0.5

- D. Stability and Density: The mixture shall be designed at or near optimum density, as indicated on the Drawings, to conform to the following percent of Maximum Theoretical Density as measured by TxDOT Test Method TEX-227-F and Stability conforming to TxDOT Test Method TEX-208-F. The laboratory mixture shall be molded in accordance with TxDOT Test Method TEX-206-F and the Bulk Specific Gravity determined in accordance with TxDOT Test Method TEX-207-F.

	Optimum Laboratory Density (%)	Laboratory Density (%)		Stability
		Min.	Max.	
Local Streets Surface Courses	96	94.5	97.5	35 Min.
Collectors & Arterials Surface Courses	96	94.5	97.5	40-60
All Base Courses	96	94.5	97.5	35 Min.

- E. Job Mix Formula Field Adjustments: The Contractor shall produce a mixture of uniform composition closely conforming to the reviewed JMF, that falls within the limits of the tolerances given above and the Acceptance Plan.

If it is determined by the City of Austin that adjustments to the JMF are necessary to achieve the specified requirements, the Engineer or designated representative may allow adjustments of the JMF within the following limits without a laboratory redesign of the mixture. The adjusted JMF shall not exceed the master grading criteria for the type of mixture specified. The proposed JMF adjustments shall not exceed 5 percent on any one sieve, ½-inch (12.5 mm) size and larger, or 3 percent on the sieve size below the 1/2-inch (12.5 mm) sieve of the JMF (Plant Corrected) reviewed for the Project.

When the proposed adjustments exceed either the 5 or 3 percent limits, and the Engineer or designated representative determines that the impact of these changes may adversely affect pavement performance, a new laboratory mixture design will be required.

The asphalt content may be adjusted with the concurrence of the Engineer or designated representative to maintain desirable laboratory density near the optimum value while achieving other mix requirements. However, increasing the asphalt content of the mixture in order to reduce pavement air voids will not be allowed. Also, if the percent air voids is determined to be less than 4 percent, adjustments shall be made to the plant production by the Contractor, within the tolerances as outlined above, so that an adequate air void level is attained.

340S.5 Equipment

The trucks that deliver the hot mix asphalt concrete material to the project shall be of sufficient number to insure a continuous paving operation. All equipment used for the production,

placement and compaction of the mixture shall be maintained in good repair and operating conditions to the satisfaction of the Engineer or designated representative. All equipment shall be made available for inspection. If the Engineer or designated representative expresses concern about the condition of any equipment, it shall not be used until it is repaired to the satisfaction of the Engineer or designated representative.

- A. **Mixing Plants:** Plants may be of the weigh-batch type, the modified weigh-batch type or drum-mix type equipped with suitable material conveyers, power units, mixing equipment, aggregate proportioning devices, dryers, bins, dust collectors and sensing and recording devices as appropriate for the mixing plant type. The mixing plants shall meet the requirements specified in Section 340.4, 'Equipment' of TxDOT Specification Item No. 340, "Hot Mix Asphaltic Concrete Pavement".
- B. **Spreading and Finishing Paving Machine:** The paving machine shall be self-propelled and equipped with a heated compacting screed capable of producing a finish surface meeting the requirements of the street cross-section indicated on the Drawings and all surface criteria. Extensions to the screed shall have the same heating and compacting capabilities as the primary unit, except for use on variable depth tapered areas and/or as approved by the Engineer or designated representative.

The paving machine shall be equipped with an approved automatic dual longitudinal screed control system and an automatic transverse screed control system. The longitudinal controls shall be capable of operating from any longitudinal grade reference including a string line, ski, mobile string line or matching shoe. Unless indicated otherwise on the Drawings, the Contractor may use any one of these grade references. The selected grade reference equipment shall be maintained in good operating condition by personnel trained in the use of the specific type of equipment.

The Contractor shall furnish all labor and equipment required for establishing and maintaining appropriate grade reference.

- C. **Rollers:** The Contractor shall select rollers conforming to Item 230S, "Rolling (Flat Wheel)" and Item 232S, "Rolling (Pneumatic Tire)". Rollers that do not conform to these requirements shall be immediately removed from the Project.
- D. **Motor Grader:** A self-propelled power motor grader may only be used, when its use is approved by the Engineer or designated representative. It shall have a blade of not less than 12 feet (3.66 meters) and a wheelbase of not less than 16 feet (4.88 meters). Smaller graders may be used for small irregular areas when approved by the Engineer or designated representative.
- E. **Material Transfer Equipment:** Equipment for transferring the HMA mixture from the hauling units or the roadbed to the spreading and finishing machine will be allowed unless indicated otherwise on the Drawings.

Windrow pick-up equipment, if permitted by the Engineer or designated representative, shall be constructed in such a manner that substantially all of the HMA mixture deposited on the roadbed is picked up and loaded into the spreading and finishing machine. The HMA mixture shall not be contaminated with foreign material. The loading equipment shall be designed so that it does not interfere with the spreading and finishing machine in obtaining the required line, grade and surface without resorting to hand finishing.

- F. **Straightedges and Templates:** The Contractor shall provide a ten-foot (3.05 meter) straightedge acceptable to the Engineer or designated representative for surface testing.

Satisfactory templates shall be provided as required by the Engineer or designated representative.

340S.6 Stockpiling Aggregates

Aggregates shall be stockpiled to facilitate blending. When the aggregate is not stockpiled on a hard, non-contaminant base, the bottom six-inch (150 mm) depth of the stockpiles shall not be used in asphaltic mixtures. Where space is limited at the plant site, the aggregate stockpiles shall be separated by walls or other appropriate barriers.

Aggregates shall be stockpiled and handled in a manner that will insure minimization of segregation and contamination. Aggregate and RAP stockpiles shall only contain material from a single source.

340S.7 Mixture Temperature

The Contractor shall select a target temperature for discharge of the HMA mixture from the mixer between 250°F (120°C) and 350°F (176°C) that is suitable to weather and Project conditions. The target temperature shall be reported to the Engineer or designated representative daily and recorded in the Daily Progress Report. The HMA mixture temperature shall not vary by more than 25°F (14°C) from the target temperature for discharge from the mixer. HMA mixtures that are discharged from the mixer at a temperature exceeding 360°F (182°C) or a temperature more than 50°F (28°C) below the target temperature shall not be accepted and shall not be placed on the Project.

340S.8 Mixture Storage

A surge-storage system may be used to minimize production interruptions during a normal day of operation. When approved by the Engineer or designated representative, overnight storage of HMA mixture in insulated storage bins may be used provided that material temperature and physical properties of the HMA mixture are not adversely affected. HMA mixtures that include hardened lumps shall not be used. Stored HMA mixtures shall not be exempt from any requirements provided in this specification.

When a surge-storage system is used, it shall be equipped with a device such as a job hopper or other device approved by the Engineer or designated representative to prevent segregation in the surge-storage bin.

340S.9 Mixture Moisture Content

Hot mix asphalt (HMA) mixtures produced from any plant shall not have a moisture content in excess of 1 percent by weight (mass) when discharged from the mixer. The moisture content shall be determined in accordance with TxDOT Test Method Tex-212-F, Part II, except that the sample shall be left in the oven a total of not less than four (4) hours.

340S10 Construction Methods

- A General: The Contractor shall be responsible for the production, transportation, placement and compaction of the specified HMA paving mixture to the requirements of this specification. The Contractor shall also be responsible for providing a safe environment for inspection personnel to inspect the equipment and to acquire samples.

All hot mix asphalt concrete pavement surface courses shall be placed with a spreading and finishing (lay-down) machine only. All hot mix asphalt concrete pavement base layers with the possible exception of the first lift of the base layer shall also be placed with a spreading and finishing (lay-down) machine. Longitudinal pavement joints shall be located under the proposed lane lines. Density tests shall be taken prior to opening to traffic.

The first lift of a base layer may be placed with a motor grader if approved in advance by the Engineer or designated representative. The loose measure thickness of this first lift shall not exceed 6 inches (150 mm). If placed with a motor grader, the first lift shall achieve a minimum in-place relative density of 89% as determined by TxDOT test procedures TEX-207-F and TEX-227-F. All subsequent lifts should be placed with a spreading and finishing (lay-down) machine and shall be subject to the requirements of Section 340S.12, "Acceptance Plan". Density tests will be taken randomly to confirm compliance with the specification requirements.

For hot mix asphalt overlays, an automatic screed shall be used with outriggers.

Any material delivered to the Project that by visual inspection can reasonably be expected not to meet specification requirements (i.e. segregated or burned material, deficient or excess asphalt, low mixing temperature, visible contaminants, etc.), as determined by the Engineer or designated representative, shall not be used or left in place.

Equipment shall be inspected prior to use and, if found to be defective or in an operating condition that could potentially affect the quality of the finished pavement, as determined by the Engineer or designated representative, its use shall not be allowed. Leakage of fuels, oils, grease, hydraulic or brake fluids or other contaminants onto the prepared surface or newly-laid HMA layer will not be allowed and may require replacement of the affected pavement area.

The HMA paving mixture, when placed with a spreading and finishing machine, shall not be placed when the air temperature is below 50°F (10°C) and is falling, but it may be placed when the air temperature is above 40°F (4°C) and is rising.

The paving mixture, when used as a level-up course or when spread with a motor grader, shall not be placed when the air temperature is below 60°F (15°C) and is falling, but it may be placed when the air temperature is 50°F (10°C) and is rising. An HMA layer with a thickness of 1-1/2 inches (37.5 mm) and less shall not be placed when the temperature of the surface on which the layer is to be placed is below 50°F (10°C). The temperature shall be taken in a shaded area away from artificial heat.

Additional surface temperature requirements may be included in the Contract Documents or indicated on the Drawings.

Surfaces to be paved shall be finished, primed, cured, broomed and tacked, as appropriate, to the satisfaction of the Engineer or designated representative. If the surface on which the first course of the paving mixture is to be placed is a flexible base course, and a cut-back asphalt is to be used as a prime coat, the flexible base shall have been primed and cured a minimum of 24 hours before the paving mixture may be placed. The 24-hour restriction will not apply to a flexible base that has been primed with material other than a cutback. However, the surface on which the tack coat and/or paving mixture are to be placed shall be in a dry condition.

Pavement shall be opened to traffic as soon as possible after temporary pavement markings or permanent markings are in place as indicated on the Drawings) or as directed by the Engineer or designated representative. Construction traffic allowed on pavements open to the public will be subject to all laws governing traffic on streets and highways.

- B. Tack Coat: The surface upon which the tack is to be placed shall be cleaned thoroughly to the satisfaction of the Engineer or designated representative. The surface shall be given a uniform application of tack coat as governed by Standard Specification Item No. 307S, "Tack Coat". The tack coat shall be applied, as directed by the Engineer or designated representative, with an approved sprayer at a rate not to exceed 0.05 gallons per square yard. (0.225 liters per square meter) of surface area. Where the paving mixture will adhere to the surface on which it is to be placed without the use of a tack coat, the tack coat may be eliminated when approved by the Engineer or designated representative. All contact surfaces of curbs, castings and all structures and all joints shall be painted with a thin uniform application of tack coat.

During the application of tack coat, care shall be taken to prevent splattering of adjacent pavement, curb and gutter and structures. Before the Work can be accepted, all splatter shall be removed by the Contractor at his own expense.

- C. Transporting Hot Mix Asphaltic (HMA) Concrete: The HMA mixture shall be hauled to the Work site in tight vehicles that were previously cleaned of all foreign material. Dispatching of the vehicles shall normally be arranged so that all material delivered is placed and all rolling completed during daylight hours. Nighttime paving may be allowed, when approved in advance by the Engineer or designated representative.

In cool weather or for long hauls, truck bodies containing the HMA mixture shall be covered.

If necessary, to prevent the HMA mixture from adhering to the truck body, the inside of the truck may be given a light coating of a release agent satisfactory to the Engineer or designated representative.

- D. HMA Placement: The HMA mixture shall be dumped and spread on the approved prepared surface with the spreading and finishing machine. When properly compacted, the finished pavement shall be smooth, of uniform texture and density and shall meet the requirements of the typical cross sections and the surface tests. In addition the placement of the HMA mixture shall be done without tearing, shoving, gouging or segregating the mixture and without producing streaks in the HMA layer.

Discharge of the HMA mixture into the finishing machine shall be controlled so that the spreading and finishing machine is not bounced or jarred and the required lines and grades shall be obtained without resorting to hand finishing except as permitted below in this Section.

Unless indicated otherwise on the Drawings, dumping of the HMA material in a windrow and then placing the HMA mixture in the finishing machine with windrow pick-up equipment will be permitted provided the temperature of the HMA mixture does not drop more than 50°F (28°C) below the target temperature before being placed by the finishing machine.

Under no circumstances will the HMA material be permitted to be dumped on or near the job site and then reloaded for hauling to the site of placement. Exceptions may be allowed if approved by the Engineer or designated representative.

The windrow pick-up equipment shall be operated in such a manner that substantially all the mixture deposited on the roadbed or prepared surface is picked up and loaded into the finishing machine without contamination by foreign material. The windrow pick-up equipment will also be so operated that the finishing machine will obtain the required line, grade and surface without resorting to hand finishing. Any operation of the windrow pick-

up equipment resulting in accumulation and subsequent shedding of accumulated material into the HMA mixture will not be permitted.

When approved by the Engineer or designated representative, level-up courses may be spread with a motor grader that meets the requirements of this specification item.

The spreading and finishing machine shall be operated at a uniform forward speed consistent with the plant production rate, hauling capability and roller train capacity to result in a continuous operation. Stopping of the spreading and finishing machine between trucks is to be held to a minimum. If, in the opinion of the Engineer or designated representative, delivery of material is adversely affecting the condition of the HMA layer (excessive stopping of the spreading and finishing machine, loss of mixture temperature, etc.), the Engineer or designated representative may require paving operations to cease until acceptable methods are provided to minimize starting and stopping of the spreading and finishing machine.

The hopper gates of the spreading and finishing machine shall be adjusted to provide an adequate and consistent flow of material. This shall result in enough material being delivered to the augers so that they are operating approximately 85 percent of the time or more. The augers shall provide means to supply adequate flow of material to the center of the paver. Augers shall supply an adequate flow of material for the full width of the mat being placed, as approved by the Engineer or designated representative. Augers should be kept approximately one-half to three-quarters full of HMA mixture at all times during the paving operation.

When the HMA mixture is placed in a narrow strip along the edge of an existing pavement, or is used to level up small areas of an existing pavement or is placed in small irregular areas where the use of a finishing machine is not practical, the finishing machine may be eliminated when permitted by the Engineer or designated representative.

The paving material adjacent to castings and flush curb and gutter and structures shall be finished uniformly high so that when compacted, it will be slightly above but not more than 1/8 inch (3 mm) above the edge of the casting or gutter lip.

Construction joints of successive courses of HMA material shall be offset at least 6 inches (150 mm). Longitudinal joints in the layer shall be placed to coincide with lane lines as directed the Engineer or designated representative. Transverse joints shall be offset a minimum of 5 feet (1.5 meters).

- E. Compaction: The pavement layers/lifts shall be compacted thoroughly and uniformly to obtain the compaction and cross section meeting the requirements indicated on the Drawings and this specification item.

Regardless of the method used for compaction, all rolling to achieve specified density shall cease before the temperature of the HMA mixture drops below 175°F (80°C).

Rolling with a pneumatic tire roller shall be used to seal the surface. Rolling with a tandem or other steel-wheel roller shall be provided if required to iron out any roller marks. Surface sealing and removal of roller marks may be accomplished at HMA temperatures below 175°F (80°C).

Vibratory rollers shall not be allowed in the vibrating mode on layers with a plan thickness less than 1-1/2 inches (37.5 mm).

The motion of the rollers shall be slow enough to avoid other than usual initial displacement. If any displacement occurs, it shall be corrected to the satisfaction of the Engineer or designated representative.

The roller shall not be allowed to stand on pavement, which has not been compacted to minimum density requirements. In order to prevent adhesion of the surface mixture to the steel-wheel rollers, the wheels shall be thoroughly moistened with water; however an excess of water will not be allowed. Necessary precautions shall be taken to prevent the dropping of diesel, gasoline, oil, grease or other foreign matter on the pavement, either when the rollers are in operation or when standing.

The edges of the pavement along curbs, headers and similar structures, and all places not accessible to the roller, or in such positions as will not allow thorough compaction with the rollers, shall be thoroughly compacted with lightly oiled tamps.

Rolling with a trench roller will be required on widened areas, in trenches and other limited areas where satisfactory density cannot be obtained with the approved rollers.

340S.11 Sampling and Testing

The HMA mixture shall be tested daily at the Project site for conformance to specification requirements. The Engineer or designated representative shall utilize a random selection method to determine sample locations based on the Contractor's anticipated production. Each day's anticipated production shall be divided into three (3) essentially equal single-pass, sub-area lots. Each day's sample locations shall be equally distributed over the three (3) sub-areas. If, due to the weather or plant malfunctions, the Contractor's daily-anticipated production is not attained, the random locations will not be recalculated. Also, no more than one location of the three (3) sub-areas shall be located in an irregular shaped area such as a cul-de-sac.

Unless directed otherwise by the Engineer or designated representative, a minimum of three bag samples and three correlating 6-inch (150-mm) cores will be obtained from each day's production.

Bag samples shall be taken during lay-down operations. The primary sampling point for the bag samples shall be from the windrow if a windrow elevator is used. If a windrow elevator is not used, the sample shall be taken from the middle of the paving machine hopper. This sampling location will require a stoppage in the paving operation in order for the Inspector to safely secure a sample from the hopper.

One core shall be taken for every 2,000 single-pass square yards (1 675 single-pass square meters) with a minimum of three (3) cores for all projects. One core shall be taken at the same station and pass sampled for each of the bag samples. Cores shall be taken by the City's laboratory within 48 hours of pavement laydown unless otherwise directed by the Engineer or designated representative.

For total areas of less than 500 square yards (420 square meters), a total of only two bag samples and two correlating cores will be obtained. If the Contractor desires additional testing, it shall be at its own entire expense.

The Engineer or designated representative may alter, increase or waive the testing schedule to ensure material and workmanship compliance with specification requirements. Acceptability of the completed pavement shall be based on the average of test results for the Project as defined in Section 340S.12, "Acceptance Plan" of this item.

Gradation, asphalt content and stability value of the HMA mixture shall be reported for each of the bag samples. The stability value reported for each of the bag samples shall be the average of three (3) tests per bag.

Pavement thickness and density shall be determined from 6-inch (150 mm) field cores. For each day's placement, density of cores for which no corresponding bag samples were taken shall be determined by using the average Maximum Theoretical Density of the day's three (3) bag samples or as may otherwise be determined by the Engineer or designated representative.

When, in the opinion of the Engineer or designated representative, test results appear unrepresentative, additional testing may be authorized. The retesting will be at the expense of the Contractor and the results of the retesting shall be averaged with the results of the original testing. If the results of retesting indicate that the original test results were erroneous, the original test results will be discarded. In the instance of erroneous original test results the subsequent first set of retests will be at the expense of the City of Austin.

Pavements with low-density results may be recored; but the pavement shall not receive any additional compactive effort.

Pavements that will not or cannot be cored within 48 hours shall be closed to both public and construction traffic.

340S.12 Acceptance Plan

For the purpose of the Acceptance Plan only, the "Paving Project" of each of the specified mixture types shall be defined by the Engineer or designated representative before the paving operation begins

Considerations for defining the Paving Project shall include paving operations staged due to traffic considerations, pavement structural section (i.e. with varying layer thicknesses), time required for paving, changes to the Job Mix Formula, phasing of large projects, or other factors affecting the consistency in the production, lay-down/compaction, use of completed portions, and/or aging of in-place material.

Acceptability of the completed pavement structure for a Paving Project shall be based on all daily averages of three test results and when approved by the Engineer or designated representative the overall average of all test results for each of the mixture/layer types specified on the Drawings.

Pay adjustments for two or more acceptance factors shall be accumulative. Pay adjustments of 100% unit price reduction shall require removal and replacement of the Work. Replacement materials shall be subject to all requirements of this specification. Alternatively, the Engineer or designated representative may allow the Work to remain in place without payment provided that the Work is warranted for an extended period under conditions as determined by the Engineer or designated representative. The decision of the Engineer or designated representative related to the removal and replacement of the Work shall be the final authority.

A. Non-Pay-Adjustment Acceptance Factors:

- 1 Surface Characteristics: Unless otherwise directed by the Engineer or designated representative, all pavements shall be tested for smoothness. Surfaces shall be tested with a 10-foot (3.05 meter) straightedge parallel to the roadway centerline and perpendicular to the centerline on flat, cross-slope sections. Maximum allowable deviation in 10 feet shall be 1/8 inch (1-mm per meter) parallel to the centerline and 1/4 inch (2-mm per meter) perpendicular to the centerline. Sections exceeding these maximums shall be corrected to the satisfaction of the Engineer or designated representative. The completed surface must meet the approval of the Engineer or designated representative for surface smoothness, finish and appearance.

If the surface ravel, ruts or deteriorates in any manner prior to the end of the warranty period, it will be the Contractor's responsibility to correct this condition at its own entire expense to the satisfaction of the Engineer or designated representative in conformance with the requirements of this specification.

For HMAC rehabilitation and overlay projects, if cracks develop in the pavement surface within the one-year warranty period, the Contractor shall seal the cracks in accordance with Standard Specification Item No. 313S, "Cleaning and/or Sealing Joints and Cracks (Asphaltic Concrete). Payment for this work will be measured and paid for as Mobilization (LS) and Crack Sealing (LF).

For new HMAC roadways constructed in accordance with the Drawings and specifications, if cracks less than 1/4 inch (6 mm) in width develop in the pavement surface within the one year warranty period the Contractor shall seal the cracks in accordance with Standard Specification Item No. 313S, "Cleaning and/or Sealing Joints and Cracks (Asphaltic Concrete). Payment for this Work will be measured and paid for as Mobilization (LS) and Crack Sealing (LF).

If cracks equal to or greater than 1/4 inch (6 mm) in width develop in the pavement surface within the one-year warranty period, the cracking shall be reviewed and evaluated by the Engineer or designated representative before corrective action is taken.

2. **Stability:** Stability test results shall be used as indicators of potential problems. Where stability test results fall below the range specified in this specification, additional tests shall be taken as directed by the Engineer or designated representative for further evaluation and monitoring of the paving mixture. This additional stability testing will be at the expense of the Contractor. When, in the opinion of the Engineer or designated representative, the stability is deemed unacceptable for the intended use of the pavement, the paving mixture shall be removed and replaced to the limits indicated by test results or may be left in place on conditions acceptable to the Engineer or designated representative. When the paving mixture is removed and replaced, it shall be at the sole expense of the Contractor.
3. **Laboratory Density:** Laboratory density results as determined by TxDOT Test Method Tex-207-F shall be used as indicators of potential problems. Where laboratory density test results are less than 94.5% or more than 97.5% of mix design maximum density, additional tests shall be taken as directed by the Engineer or designated representative for further evaluation and monitoring of the paving mixture. This additional laboratory density testing will be at the expense of the Contractor. When, in the opinion of the Engineer or designated representative, the laboratory density is deemed unacceptable for the intended use of the pavement, the paving mixture shall be removed and replaced to the limits indicated by test results.

The removal and replacement of the paving mixture shall be at the sole expense of the Contractor.

4. **Limited Areas:** Irrespective of an acceptable overall Paving Project average for any or all of the Pay-Adjustment Acceptance Factors, limited substandard portions of the Work, as determined by the Engineer or designated representative, shall be remedied or removed and replaced to the satisfaction of the Engineer or designated representative at the sole expense of the Contractor.
- B. **Pay-Adjustment Acceptance Factors:** Contract unit prices shall be adjusted for paving mixtures that fail to meet acceptance criteria for gradation, asphalt content, density and mat thickness in accordance with the following:

Gradation Acceptance Schedule (TEX-210-F)

Sieve	Deviation From Job Mix Formula		Percent Contract Unit Price Reduction
	Daily Average	Overall Average	
Total retained on No. 10 (2.00 mm)	± 6.5	± 5.0	0
	6.6±	5.1±	10
Passing No. 200 (75 µm)	± 3.9	± 3.0	0
	4.0±	3.1±	5

Asphalt Content Acceptance Schedule (TEX-210-F, PartII)

Deviation from the Job Mix Formula		Percent Contract Unit Price Reduction	
Daily Average	Overall Average	Local Streets*	All Others
± 0.5	± 0.4	0	0
±0.51 to ±0.60	±0.41 to ±0.50	15	25
+0.61 to +0.70	+0.51 to +0.60	25**	100; Remove and Replace
-0.61 to -0.70	-0.51 to -0.60	100; Remove and Replace	100; Remove and Replace
Over ±0.70	Over ±0.60	100; Remove and Replace	100; Remove and Replace

*A local or residential street that serves as access to residence or other abutting property.
**If the street has an ADT of 500, or less, with 1%, or less, of truck traffic, plus a 2 year warranty; otherwise, Remove and Replace

Density Acceptance Schedule (TEX-207-F/TEX-227-F)

*Percent Density		Percent Contract Unit Price Reduction	
Daily Average	Overall Average	1-1/2" (38 mm) Thickness or Greater	Less than 1-1/2" (38 mm) Thickness
Above 96.5	Above 96	100; Remove and Replace	100; Remove and Replace
90.5 to 96.5	91 to 96	0	0
90.5 to 87.6	90.9 to 88.1	0.625 per 0.10% deficiency in density	0.50 per 0.10% deficiency in density
Less than 87.6	Less than 88.1	100; Remove and Replace	100; Remove and Replace

*Core bulk density divided by max. theoretical density

Thickness Acceptance Schedule

Variance Percent of Thickness	Percent Contract Unit Price Reduction
-------------------------------	---------------------------------------

Daily Average	Overall Average	
0 – 15.0	0 - 10	0
15.1 – 20.0	10.1 - 16	20
20.1 – 30.0	16.1 - 25	50
Over 30.0	Over 25	100; Remove and Replace or mill/overlay 1" (25 mm) minimum

The Density Acceptance Schedule For Irregularly Shaped Areas; Hike And Bike Trails And Utility Trenches (see following table) will apply to utility trenches of widths less than 4 feet (1.2 meter) and to irregular shaped areas and hike and bike trails in which an appropriate rolling pattern cannot be established making it difficult to achieve compaction.

Density Acceptance Schedule For Irregularly Shaped Areas; Hike And Bike Trails and Utility Trenches (TEX-207-F/TEX-227-F)

*Percent Density	Percent Contract Unit Price Reduction	
Daily Average	1-1/2" (38 mm) Thickness or Greater	Less than 1-1/2" (38 mm) Thickness
Above 96.5	100; Remove and Replace	100; Remove and Replace
96.5 to 89.0	0	0
89.0 to 86.1	0.625 per 0.10% deficiency in density	0.50 per 0.10% deficiency in density
Less than 86.1	100; Remove and Replace	100; Remove and Replace
*Core bulk density divided by maximum theoretical density		

The Density Acceptance Schedule will apply to utility trenches 4 feet (1.2 meter) or wider.

Core thicknesses greater than Drawing requirements shall be factored into the average thickness calculation as the Drawing required thickness. If total thickness of lift(s) proves to be less than required, the Contractor may remove and replace the overlay deficient areas as agreed to by the Engineer or designated representative. Overlays to correct thickness deficiencies shall be not less than one (1) inch (25-mm) thick. Overlays shall require milling of the asphalt in order to prevent a "featheredge" of the overlaying pavement.

The extent of the area to be overlaid or removed and replaced shall be determined by additional cores with thicknesses greater than or equal to the required thickness. All additional coring that is necessary to determine the area shall be paid for by the Contractor.

340S.13 Measurement

Work performed and material placed shall be measured under one of the following methods. When Drawing quantity measurement is specified, adjustment of quantity may be made as follows. If the quantity measured as outlined vary from those shown on the Drawings by more than 5%, either party to the Contract may request in writing and adjustment of the quantity by each separate bid item. The party to the Contract which requests the adjustment shall present to the other party one copy of measurements and calculations showing the revised quantity in question. This revised quantity, when approved by the Engineer or designated representative, shall constitute the final quantity for which payment will be made. However, no adjustment will be made for any quantity, which exceeds the Drawing required thickness.

- A. Method A: Asphaltic concrete pavement shall be measured by the ton (2,000 pounds) of the type actually used in completed and accepted Work in accordance with the Drawings and specifications.

The measurement shall be made on approved truck scales that meet the requirements of the National Institute of Standards and Technology Handbooks 44 and 112 except that the required accuracy shall be 0.4 percent of the load being weighed. The Contractor shall furnish a report of calibration from a scale mechanic licensed by the Texas Department of Agriculture certifying that the scales meet this requirement.

- B. Method B: Asphaltic concrete pavement shall be measured by the square yard of specified total thickness of the type of paving mixture actually used in completed and accepted Work in accordance with Drawings and specifications. Multiple lifts of the same type shall be considered as one for square yard measurement purposes.

- C. Method C: Asphaltic concrete pavement shall be measured by the lineal foot of specified total thickness of the type of paving mixture actually used in completed and accepted Work in accordance with Drawings and specifications. Multiple lifts of the same type shall be considered as one for linear foot measurement purposes.

340S.14 Payment

Work performed and materials furnished as prescribed by this item and measured as provided under "Measurement" will be paid for at the unit bid prices or pay adjusted unit price for Hot Mix Asphaltic Concrete Pavement, of the types and thicknesses specified. The unit bid prices shall include full compensation for furnishing all labor, equipment, time, materials and incidentals necessary to complete the Work.

Removal of existing hot mix asphalt concrete transition areas prior to overlay, tack coat, saw cutting and temporary pavement markings will not be measured or paid for directly but shall be included in the unit price bid for Standard Specification Item No. 340S, "Hot Mix Asphaltic Concrete Pavement".

Payment for Work meeting these specifications will be made under one of the following:

- Pay Item No. 340S-A: Hot Mix Asphaltic Concrete Pavement, Per Ton.
Type _____,
- Pay Item No. 340S-B: Hot Mix Asphaltic Concrete Pavement, Per Square Yard
____Inches, Type _____.
- Pay Item No. 340S-C: Hot Mix Asphaltic Concrete Pavement, Per Lineal Foot.
____Inches, Type _____.
- Pay Item No. 340S-PQ: Hot Mix Asphaltic Concrete Pavement, ~~Per Ton.~~ ~~Per~~
____Inches, Type _____, ~~Plan Quantity~~ ~~Drawing Quantity~~
- Pay Item No. 340S-L: Hot Mix Asphaltic Concrete Pavement, Lump Sum.
____Inches, Type _____, Level-up
Course.
- Pay Item No. 340S-M: Crack Sealing Mobilization, Lump Sum.
- Pay Item No. 340S-S: Crack Sealing, Per Lineal Foot.

End

<i>SPECIFIC</i> CROSS REFERENCE MATERIALS
Special Specification Item 340S "Hot Mix Asphaltic Concrete Pavement"

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 230S	Rolling (Flat Wheel)
Item No. 232S	Rolling (Pneumatic Tire)
Item No. 301S	Asphalts, Oils and Emulsions
Item No. 307S	Tack Coat
Item No. 313S	Cleaning and/or Sealing Joints and Cracks (Asphaltic Concrete)

Texas Department of Transportation: Manual of Testing Procedures

<u>Designation</u>	<u>Description</u>
Tex-106E	Method of Calculating the Plasticity Index of Soils
Tex-107E	Determination of Bar Linear Shrinkage of Soils
Tex-200-F	Sieve Analysis of Fine and Coarse Aggregates
Tex-203-F	Sand Equivalent Test
Tex-204-F	Design of Bituminous Mixtures
Tex-207-F	Determination of Density of Compacted Bituminous Mixtures
Tex-208-F	Test for Stabilometer Value of Bituminous Mixtures
Tex-210-F	Determination of Asphalt Content of Bituminous Mixtures by Extraction
Tex-212-F, Part II	Determination of Moisture Content of Bituminous Mixtures (by oven drying)
Tex-217-F	Determination of Deleterious Material and Decantation Test For Coarse Aggregates
Tex-227-F	Theoretical Maximum Specific Gravity of Bituminous Mixtures
Tex-410-A	Abrasion of Coarse Aggregate Using the Los Angeles Machine
Tex-460-A	Determination of Crushed Face Particle

Texas Department of Transportation: Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges

<u>Designation</u>	<u>Description</u>
Item 340	Hot Mix Asphalt Concrete Pavement

<i>RELATED</i> CROSS REFERENCE MATERIALS
Special Specification Item 340S "Hot Mix Asphaltic Concrete Pavement"

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 206S	Asphalt Stabilized Base
Item No. 210S	Flexible Base
Item No. 306S	Prime Coat

Item No. 310S Emulsified Asphalt Treatment
Item No. 311S Emulsified Asphalt Repaving
Item No. 320S Two Course Surface Treatment

Texas Department of Transportation: Manual of Testing Procedures

<u>Designation</u>	<u>Description</u>
Tex-215-F	Determination of Asphalt Content of Rock Asphalt By Hot Solvent Method
Tex-224-F	Determination of Flakiness
Tex-400-A	Method of Sampling Stone, Gravel, Sand and Mineral Aggregates
Tex-411-A	Soundness of Aggregate by Use of Sodium Sulfate or magnesium Sulfate
Tex-438-A	Accelerated Polish Test for Aggregate

Item No. 401S
Structural Excavation and Backfill

401S.1 Description

This item shall govern the excavation for placement of structures, except pipe sewers, the disposal of such excavated material and the backfill around completed structures to the level of the original ground or grade indicated on the Drawings. The work shall include all necessary pumping or bailing, sheathing, drainage, and the construction and removal of any required cofferdams. Unless otherwise indicated on the Drawings, the work included hereunder shall provide for the removal of old structures or portions thereof (abutments, buildings, foundations, wingwalls, piers, etc.), trees and all other obstructions necessary to the proposed construction.

Where excavation is not classified, it will be grouped under "Unclassified Structural Excavation", which shall include the removal of all materials encountered regardless of their nature or the manner in which they are removed.

Where excavation is classified, it shall be classed as "Common Structural Excavation" or "Rock Structural Excavation" in accordance with the following criteria:

"Common Structural Excavation" shall include the removal of all materials other than rock.

"Rock Structural Excavation" shall include the removal of firm and compact materials that cannot be excavated with power equipment, without first being loosened or broken by blasting, sledging or drilling.

This specification is applicable for projects or work involving either inch-pound or SI units. Within the text and accompanying tables, the inch-pound units are given preference followed by SI units shown within parentheses.

401S.2 Submittals

The submittal requirements of this specification item may include:

Supplier and certified test results for fine aggregate/sand material

Supplier and certified test results for flexible base material

Mix design and test results for lime stabilized subgrade material

Mix design and test results for Class J Concrete Base

Supplier and certified test results for granular material (coarse aggregate, foundation rock and pea gravel)

Mix design and test results for cement-stabilized backfill

Mix design and test results for controlled low strength material (CLSM)

Excavation Safety System Plan for proposed cofferdams, trench excavation and special shoring installations

401S.3 Materials

A. Sand

1. Fine aggregate sand shall be Grade 1 conforming to Standard Specification Item No. 302S, "Aggregates for Surface Treatments".
2. Native Sand shall be local material obtained from approved sources and subject to the approval of the Engineer or designated representative.

B. Flexible Base

Flexible base shall conform to the requirements of Standard Specification Item No. 210S, "Flexible Base".

C. Lime Stabilized Base

Lime stabilized base shall conform to the requirements of Standard Specification Item No. 202S, "Hydrated Lime and Lime Slurry" and Item No. 203S, "Lime Treatment for Materials in Place".

D. Concrete Base

Concrete base shall conform to a Class J Concrete as defined in Standard Specification Item No. 403S, "Concrete for Structures".

E. Granular Material

1. Coarse aggregate shall conform to the requirements of section 403S.3.C of Standard Specification Item No. 403S "Concrete for Structures".

2. Foundation Rock

Foundation rock shall be well graded, hard, durable coarse aggregate ranging in size from 2 to 6 inches (50 to 150 mm).

3. Pea Gravel

Pea gravel shall consist of hard, durable, opaque gravel, free of clay, loam, sand or other foreign substances, ranging in size from 1/4 inch to 3/8 inch (6.4 to 9.5 mm) conforming to ASTM C 33.

F. Cement Stabilized Backfill

Cement stabilized backfill shall contain aggregate, water and a minimum of 7% hydraulic cement based on the dry weight of the aggregate in accordance with TxDOT Test Method Tex-120-E, "Soil-Cement Testing". Unless directed otherwise on the Drawings, the aggregate shall be clean sand approved by the Engineer or designated representative.

G. Controlled Low Strength Material

Controlled low strength material (CLSM) shall conform to Standard Specification Item No. 402S, "Controlled Low Strength Material" and shall be approved by the Engineer or designated representative.

401S.4 Construction Methods

A. Erosion Control and Tree Protection

Prior to commencement of this work, all required erosion control and tree protection measures indicated on the Drawings shall be in place. The existing utilities shall be located

and protected as specified in the Standard Contract Documents, Section 00700, "General Conditions" and/or indicated on the Drawings. A permit shall be required when utility adjustments are to be made in preparation for construction in the right-of-way, as specified in Section 5.2.0 of the City of Austin Utilities Criteria Manual.

Areas within the construction limits indicated on the Drawings shall be cleared of all trees, stumps, brush, etc., except trees or shrubs scheduled for preservation which shall be carefully trimmed as directed by the Engineer or designated representative, in accordance with Standard Specification Item No. 610S, " Preservation of Trees and Other Vegetation" and shall be protected from scarring, barking or other injuries during construction operations. All exposed cuts over 2 inches (50 millimeters) in diameter, exposed ends of pruned limbs or scarred bark shall be treated with an approved asphalt material within 24 hours of the pruning or injury.

Construction equipment shall not be operated nor construction materials stockpiled under the canopies of trees, unless otherwise indicated on the Drawings and/or specified in the Contract Documents. Excavation or embankment materials shall not be placed within the drip line of trees until tree wells are constructed.

Within the construction limits or areas indicated, all obstructions, stumps, roots, vegetation, abandoned structures, rubbish and objectionable material shall be removed to the following depths:

1. In areas to receive 6 inches (150 mm) or more embankment, a minimum of 12 inches (300 mm) below natural ground.
2. In areas to receive embankment less than 6 inches (150 mm), a minimum of 18 inches (450 mm) below the lower elevation of embankment, structure or excavation.
3. In areas to be excavated a minimum of 18 inches (450 mm) below the lower elevation of the embankment, structure or excavation.
4. In all other areas a minimum of 12 inches (300 mm) below natural ground.

When abandoned storm drains, sewers or other drainage systems are encountered they shall be removed as required to clear the new structure and plugged in a manner approved by the Engineer or designated representative.

Holes remaining after removal of all obstructions, objectionable material, trees, stumps, etc. shall be backfilled with select embankment material and compacted by approved methods. All cleared and grubbed material shall be disposed of in a manner satisfactory to the Engineer or designated representative. Unless otherwise provided, all materials as described above shall become the property of the Contractor and removed from the site and disposed of at a permitted disposal site.

Burning materials at the site shall conform to Standard Contract Document Section 01550, "Public Safety and Convenience".

B. Excavation

1. Excavation shall be done in accordance with the lines and depths indicated on the Drawings or as established by the Engineer or designated representative. Unless otherwise indicated on the Drawings or permitted by the Engineer or designated representative no excavation shall be made outside a vertical plane 3 feet (0.9 meter) from the footing lines and parallel thereto.

When structures are installed in streets, highways or other paved areas, the pavement and base shall be cut to neat lines. After completion of the excavation and backfilling, the pavement structure shall be restored to the satisfaction of the Engineer or designated representative.

2. Slopes, benching, sheeting, bracing, pumping and bailing shall be provided as necessary to maintain the stability and safety of excavations up to 5 feet (1.5 meters) deep. Excavation protection for excavations deeper than 5 feet (1.5 meters) shall be governed by Standard Specification Item No. 509S, "Excavation Safety Systems".
3. Excavation shall conform to elevations indicated on the Drawing or raised or lowered by written order of the Engineer or designated representative, when such alterations are judged proper. When it is deemed necessary to increase or decrease the plan depth of footings, the alterations in the details of the structure shall be as directed by the Engineer or designated representative. The Engineer or designated representative shall have the right to substitute revised details resulting from consideration of changes in the design conditions.
4. When a structure is to rest on an excavated surface other than rock, special care shall be taken not to disturb the bottom of the excavation and the final excavation to grade shall not be performed until just before the footing is placed. Equipment selected and used by the Contractor for excavation which results in disturbance of what was otherwise stable subgrade material, as shown by laboratory tests, will not be used as a justification for payment for excavating to extra depth or for payment for stabilizing materials which may be ordered by the Engineer or designated representative.
5. Excavated material required to be used for backfill may be deposited by the Contractor in storage piles as indicated on the Drawing or at points convenient for its rehandling during the backfilling operations, subject to the approval of the Engineer or designated representative, who may require that the survey center line of the structure and the transverse or hub line of any unit of the structure be kept free of any obstruction. The Contractor shall adjust any stockpiles, to facilitate surveying and the work of other Contractors working in the immediate proximity, as directed by the Engineer or designated representative.
6. Excavated material required to be wasted shall be disposed of as directed by the Engineer or designated representative, in a manner which will not obstruct the stream or otherwise impair the efficiency or appearance of the structure or other part of the work.
7. For all single and multiple box culverts, pipe culverts, pipe arch culverts and box sewers of all types, where the soil encountered at established footing grade is a quicksand, muck or similar unstable material, the following procedure shall be used unless other methods are indicated:
 - a) The depth to which unstable material is removed will be determined by the Engineer or designated representative. It will not exceed 2 feet (0.6 meter) below the footing of culverts that are 2 feet (0.6 meter) or more in height and will not exceed the height of culverts for those less than 2 feet (0.6 meter) high. Excavation shall be carried at least 1 foot (0.3 meter) horizontally beyond the limits of the structure on all sides. All unstable soil removed shall be replaced with suitable stable material, in uniform layers of suitable depth for compaction as directed by the Engineer or designated representative. Each layer shall be wetted, if necessary and compacted by rolling or tamping as required to provide a stable foundation for the structure. Soil, which has

sufficient stability to properly sustain the adjacent sections of the roadway embankment, will be considered a suitable foundation material.

- b) When, in the opinion of the Engineer or designated representative, it is not feasible to construct a stable footing as outlined above, the Contractor shall construct it by the use of special materials, such as flexible base, cement stabilized base, cement stabilized rockfill or other material, as directed by the Engineer or designated representative. This work will be paid for as provided in Section 401S.9, " Payment".
8. When the material encountered at footing grade of a culvert is found to be partially rock or incompressible material and partially a compressible soil which is satisfactory for the foundation, the incompressible material shall be removed for a depth of 6 inches (150 mm) below the footing grade and backfilled with a compressible material similar to that used for the rest of the structure.
9. When the material encountered at footing grade of a bridge bent or pier is found to be partially of rock or incompressible material, and partially of a compressible material, the foundation shall not be placed until the Engineer or designated representative has inspected the footing and authorized such changes found necessary to provide an adequate foundation.

401S.5 Bridge Foundations and Retaining Walls

The material below the bottom of the footing grade shall not be disturbed. Backfill material shall not be used to compensate for excavation that is extended below the proposed footing grade. When excavation is carried below the proposed footing grade, the over excavated area shall be filled with concrete at the time the footing is placed. The additional concrete placement shall be at the Contractor's sole expense.

When required by the Engineer or designated representative, cores shall be taken to determine the character of the supporting material(s). The cores shall be taken when the excavation is nearing completion and shall be an intact sample adequate to judge the character of the founding material. The cores shall be acquired at a minimum depth of 5 feet (1.5 meters) below the proposed footing founding grade.

When the founding stratum is rock or other hard material, all loose material shall be removed and the founding grade cleaned and cut to a firm surface that is level, stepped or serrated as directed by the Engineer or designated representative. All soft seams shall be cleaned and filled with concrete at the time the footing is placed.

When the material at the footing grade of a retaining wall, bridge bent or pier is a mixture of compressible and incompressible material, the foundation shall not be placed until the Engineer or designated representative has inspected the excavation and authorized changes to provide a uniform bearing condition.

401S.6 Cofferdams

The term cofferdams, whenever used in this specification, designates any temporary or removable structure constructed to hold the surrounding earth, water or both, out of the excavation, whether the structure is formed of earth, timber, steel, concrete or a combination of these. It includes earthen dikes, timber cribs, any type of sheet piling, removable steel shells and the like and all necessary bracing and it shall be understood also to include the use

of pumping wells or well points for de-watering. The cost of cofferdams, when required, shall be included as a part of the bid price for excavation.

It is the intent of this specification to require that a suitable cofferdam be provided, when necessary, to insure that the foundation may be placed in a dry condition, as to preclude sliding and caving of the walls of the excavation. The cofferdam shall conform with the requirements of Standard Specification Item No. 509S, "Excavation Safety Systems" and shall provide a safe work area with sufficient clearance for the construction, inspection and removal of required forms and, if necessary, sufficient room to allow pumping outside the forms. Where no ground or surface water is encountered, the cofferdam need be sufficient only to protect the workmen and to avoid cave-ins or slides beyond the excavation limits.

Unless otherwise indicated on the Drawings, cofferdams shall be removed by the Contractor after the completion of the substructure without disturbing or marring the structure.

401S.7 De-Watering

Structures shall not be constructed or placed in the presence of water unless otherwise approved by the Engineer or designated representative. Precast members, pipe and concrete shall only be placed on a dry, firm surface. Water shall be removed by bailing, pumping, well-point installation, deep wells, underdrains or other approved method.

When structures are approved for placement in the presence of water, standing water shall be removed in a manner that shall preclude the possibility of the movement of water through or alongside any concrete being placed. Pumping or bailing will not be permitted during the placing of concrete or for a period of at least 36 hours thereafter, unless from a suitable sump separated from the concrete work by a water-tight wall.

Pumping or bailing during placement of seal concrete shall only be allowed to the extent necessary to maintain a static head of water within the cofferdam. De-watering inside a sealed cofferdam shall not commence until the seal has aged a minimum of 36 hours.

When the bottom of an excavation cannot be de-watered to the point that the subgrade is free of mud or it is difficult to keep the reinforcing steel clean a stabilizing material (e.g. flexible base, cement-stabilized-backfill or lean concrete) shall be placed in the bottom of the excavation. When a lean concrete is used, the concrete shall include a minimum of 275 Pounds of cement per cubic yard (163 kilograms of cement per cubic meter) and be placed to a minimum depth of 3 inches (75 mm). Stabilizing material that is placed for the convenience of the Contractor will be at the Contractor's own expense.

401S.8 Backfilling

A. General

As soon as practicable, all portions of excavation not occupied by the permanent structure shall be backfilled. Back-fill material shall be free from stones large enough to interfere with compaction, large or frozen lumps that will not break down readily under compaction, wood or other extraneous material. Backfill material shall be approved by the Engineer or designated representative.

That portion of backfill which will support any portion of completed roadbed, retaining wall or embankment shall be placed in layers not more than 8 inches (200 mm) in depth (loose measurement) and shall be compacted to meet the density requirements of the roadbed, retaining wall, embankment material, or as indicated on the Drawings.

That portion of backfill which will not support any portion of completed roadbed or embankment shall be placed in layers not more than 10 inches (250 mm) in depth (loose measurement) and shall be compacted to a minimum of 95 percent of maximum density as determined by TxDOT Test Method Tex-114-E and the re-excavated to the proper grade and dimensions.

If the excavation has been made through a hard material resistant to erosion, the backfill around piers and in front of abutments and wings may be ordered by the Engineer or designated representative to be of stone or lean concrete. Unless otherwise indicated on the Drawings, such backfill shall be paid for as extra work.

That portion of the backfill which will support any portion of the roadbed, retaining wall or embankment shall be placed in uniform layers not more than 8 inches (200 mm) in depth (loose measurement) and shall be compacted to a minimum of 95 percent of maximum density, as determined by TxDOT Test Method Tex-114-E and then re-excavated to the proper grade and wetted uniformly to the moisture content required to obtain the specified density and shall be compacted to that density by means of mechanical tampers or rammers, except that the use of rolling equipment of the type generally used in compaction embankments will be permitted on portions which are accessible to such equipment.

All portions of embankment too close to any portion of a structure to permit compaction by the use of the blading and rolling equipment used on adjoining sections of embankment, shall be placed and compacted with mechanical tamps and rammers to avoid damage to the structure.

These provisions require mechanical compaction by means of either rolling equipment or mechanical tampers or rammers, of all backfill and embankment adjoining the barrels and wingwalls or culverts and adjoining all sides of bridge abutments and retaining walls, regardless of whether or not such embankment or backfill is above or below the original surface of the ground and regardless of whether the excavation at structure site was performed conforming to Standard Specification Item No. 111S, "Excavation", this item 401S, "Structural Excavation", Standard Specification Item No. 110S, "Street Excavation" or Standard Specification Item No. 120S, "Channel Excavation". Unless otherwise indicated on the Drawings, hand tamping will not be accepted as an alternate for mechanical compaction.

As a general rule, material used in filling or backfilling the portions described in this paragraph shall be an earth, free of any appreciable amount of gravel or stone particles larger than 4 inches (100 mm) in greater dimension and of a gradation that permits thorough compaction. When, in the opinion of the Engineer or designated representative, such material is not readily available, the use of rock or gravel mixed with earth will be permitted, provided that no particles larger than 12 inches (300 mm) or smaller than 6 inches (150 mm) may be used. The percentage of fines shall be sufficient to fill all voids and insure a uniform and thoroughly compacted mass of proper density. When required by the Drawings or by written order of the Engineer or designated representative, cement-stabilized-backfill material shall be used for backfilling.

All portions of fill and backfill described in the preceding paragraph shall be compacted to the same density requirements specified for the adjoining sections of embankment in accordance with the governing specifications. Where no embankment is involved on the project and no relevant specifications are included in the contract, all backfill shall be compacted to a density comparable with the adjacent undisturbed material.

No backfill shall be placed against any abutment or retaining wall until such structure has been in place at least 7 days. No backfill shall be placed adjacent to or over single and multiple boxes until the top slab has attained 500 psi (3450 kPa) flexural strength. Backfill placed around abutments and piers shall be deposited on both sides to approximately the same elevation at the same time.

Care shall be taken to prevent any wedging action of backfill against the structure and the slopes bounding the excavation shall be stepped or serrated to prevent such action. Backfill shall be uniformly placed around bridge foundations.

B. Pipe Culverts

The following requirements shall apply to the backfilling of pipe culverts in addition to the pertinent portions of the general requirements given in the preceding section.

Selected materials from excavation, borrow or other approved material shall be wetted, if required and placed along both sides of the pipe equally, in uniform layers not exceeding 8 inches (200 mm) in depth (loose measurement) and thoroughly compacted so that there shall be a berm of thoroughly compacted material on each side of the pipe. The method and degree of compaction shall be the same as specified above for portions of backfill within the limits of embankment or roadbed.

Filling and/or backfilling shall be continued in this manner to the elevation of the top of the pipe. Special care shall be taken to secure thorough compaction of the material placed under the haunches of the pipe to prevent damage or displacement of the pipe. All fill or backfill below the top of pipe shall be compacted mechanically in the manner and to the density prescribed above, regardless of whether or not such material is placed within the limits of the embankment or roadbed. In the case of pipe placed in trenches, that portion of the backfill above the top of the pipe which supports embankment or the roadbed shall receive mechanical compaction as specified above and the portion which will not support any portion of embankment or roadbed shall be placed in layers not more than 8 inches (200 mm) in depth (loose measurement) and shall be compacted by whatever means the Contractor chooses, to a density comparable with the adjacent, undisturbed material. Embankments above the top of pipe shall be placed conforming to Item No. 132S, "Embankment". During construction adequate cover must be provided to protect the structure from damage.

The Engineer or designated representative may reject backfill material that contains more than 20% by weight of material retained on a 3-in (75 mm) sieve, with large lumps not easily broken down, or that cannot be spread in loose layers. Material excavated by a trenching machine will generally meet the requirements of this Section as long as large stones are not present.

Where pipe extends beyond the toe of slope of the embankment and the depth of cover provided by backfill to the original ground level is less than the minimum required by the

specifications for the type of pipe involved, additional material shall be placed and compacted until the minimum cover has been provided.

Whenever excavation is made for installing pipe culverts or box sewers across private property or beyond the limits of the embankment, the top soil removed in excavating the trench shall be kept separate and replaced as nearly as feasible in its original position and the entire area involved in the construction operations shall be restored to a presentable condition.

C. Cement Stabilized Backfill

When indicated on the Drawings, trenches shall be backfilled to the elevations shown with cement stabilized backfill. The cement-stabilized backfill shall be placed equally along the sides of structures to prevent strain on or displacement of the structure.

Cement stabilized backfill below the spring line of pipe culverts shall be sufficiently plastic to completely fill all voids in the trench. Hand operated tampers may be used if necessary to fill the voids. The pipe shall be held in alignment by jacks or other suitable means to prevent the mortared joints from cracking due to displacement caused by placing the backfill material.

Cement stabilized backfill above the spring line of pipe culverts may be dry enough to be transported without special mixing equipment.

On structures other than pipe culverts, special mixing equipment will not be required to transport the cement stabilized backfill unless otherwise indicated on the Drawings.

D. Controlled Low Strength Material (CLSM)

When indicated on the Drawings the excavation shall be backfilled with CLSM to the elevations shown. The structure shall be prevented from being displaced or "floated out" during the placement of CLSM. The CLSM shall be prevented from entering culverts and drainage structures.

401S.9 Measurement

Unless otherwise indicated on the Drawings, structural excavation for pipe headwalls, inlets, manholes, culvert widening (extensions), bridge abutments and side road and private entrance pipe culverts will not be measured but shall be included in the unit price bid **by the cubic yard for this specification item. (cubic meters: 1 cubic meter is equal to 1.308 cubic yards) or by the square yard (square meter: 1 square yard equals 0.836 square meters).** Determination of quantities for structural excavation shall be made by the method of average end-areas using the following limits to establish templates for measurement.

- A. For all structures requiring measurement, except the barrels of pipe culverts, no material outside of vertical planes 1 foot (300 mm) beyond the edges of the footings and parallel thereto will be included.
- B. For the barrels of pipe culverts of 42 inches (1.09 meters) or less nominal or equivalent diameter, no material outside of vertical planes 1 foot (300 mm) beyond the horizontal projection of the outside surfaces of the pipe and parallel thereto will be included. For the

barrels of pipe culverts more than 42 inches (1.09 meters) in nominal or equivalent diameter, no material outside of vertical planes located 2 feet (600 mm) beyond the horizontal projection of the outside surfaces of the pipe and parallel thereto will be included.

- C. If a cofferdam, as herein defined, is used, the limitations indicated above shall apply just as if no cofferdams were used.
- D. Where excavation in addition to that allowed for the footings is required for other portions of the structure, such as for the cap, cross strut or tie beam of a pier or bent or for the superstructure, measurements for such additional excavation will be limited laterally by vertical planes 1 foot (300 mm) beyond the face of the member and parallel thereto and vertically to a depth of 1 foot (300 mm) below the bottom of such member.
- E. Except as allowed by the above conditions, no account will be taken of any excavation necessary for placing forms or falsework.
- F. Except at side road culverts, all street excavation called for on the contract drawings at all structure sites shall be assumed to be completed before starting the structural excavation and the measurement of structural excavation will include only material below or outside the limits of the completed street excavation. Excavation for side road and private entrance pipe culverts will not be measured for payment but shall be included in the unit price bid for this specification item.
- G. On all structures of bridge classification where the contract drawings call for channel excavation at the structure site, it shall be assumed to have been completed before starting the structural excavation and the measurement of structural excavation will include only material below or outside the limits of the completed channel section. The method of measurement for payment will be in accordance with this procedure regardless of the actual construction methods followed.
- H. Where excavation diagrams are indicated on the Drawings, they shall take precedence over these provisions.
- I. Measurement will not include materials removed below footing grades to compensate for anticipated swellage due to pile driving and it will not include material required to be removed due to swellage beyond the specified limits during pile driving operations.
- J. Measurement will not include additional yardage caused by slips, slides, cave-ins, siltings or fillings due to the action of the elements or the carelessness of the Contractor. Water will not be classed as excavated material.
- K. Where rock, other incompressible or unstable material is undercut to provide suitable foundation for pipe or box culverts, such material below grade, ordered by the Engineer or designated representative to be removed, will be measured for payment.
- L. Except for any required undercut, quantities for "Structural Excavation", as indicated on the Drawings, shall be considered as final quantities and no further measurement will be required, unless the alignment, grades or structure locations are revised by the Engineer or designated representative during construction. Final determination of quantities for individual structures will be made, if in the opinion of the Engineer or designated representative or upon evidence furnished by the Contractor, substantial variations exist between quantities indicated on the Drawings and actual quantities due to changes in cross sections or apparent errors. Excavation quantities for foundations indicated on the Drawings where cofferdams are required shall be considered as final quantities and no further measurement will be made.

- M. For any footing, foundation or other structure unit within the scope of this specification, additional measurement will be made of the volume of excavation involved in the lowering or raising of the elevation of a footing, foundation or structure unit, when such grade change is authorized by the Engineer or designated representative. Measurement will be made by the addition to or the deduction from, the original quantities for the volume of excavation involved in the authorized grade change.
- N. Cement stabilized backfill shall be measured by the backfill diagram as indicated on the Drawings. The quantity of "Cement Stabilized Backfill" as indicated on the Drawings shall be considered as final quantities and no further measurement will be required, unless alignment or grade elevations as indicated are revised by the Engineer or designated representative. If such revisions result in an increase or decrease in this quantity, the final quantity will be revised by the amount represented by the changes in alignment or grade elevations.

401S.10 Payment

Payment for all work prescribed under this item and measured as provided above will be made at the unit bid price per cubic yard for the particular class of excavation specified on the Drawings in the amount shown on the Drawings and in the proposal. Payment for revised quantities will be made as specified above and for the removal of unstable and incompressible material as noted below.

Payment for removal and replacement of unstable or incompressible material below the footing grades of culverts and box sewers as indicated above will be made as follows:

When indicated on the Drawings or the Engineer or designated representative directs the use of special materials such as flexible base, concretebase, cement stabilized backfill, controlled low strength material or other special material, payment for excavation below the footing grades shall be made at the unit bid price for "Unclassified Structural Excavation", "Common Structural Excavation" or "Rock Structural Excavation", as the case may be. Payment for furnishing, hauling, placing and compacting the flexible base, concretebase, cement stabilized backfill, controlled low strength material or other special material will be made at the unit bid price for these items in the bid or in accordance with pertinent provisions for extra work.

Where special materials are not required or specified, the removal and replacement of the unstable material will be performed as described above. Payment therefore will be made at a price equal to 200 percent of the unit bid price per cubic yard for "Unclassified Structural Excavation", "Common Structural Excavation" or "Rock Structural Excavation", as the case may be. The unit bid price shall include full compensation for removing the unstable or incompressible material, for furnishing, hauling, placing and compacting suitable material required to replace it and for all labor, equipment, tools and incidentals necessary to complete the work.

Payment for "Concrete Base", "Cement Stabilized Backfill" and "Controlled Low Strength Material" measured as prescribed above shall be made at the unit bid price per cubic yard. The unit bid price shall include full compensation for furnishing all materials, tools, labor, equipment, sheathing and incidentals required to perform the applicable work prescribed herein.

When the Engineer or designated representative judges it necessary to lower the structure footings to an elevation below the grade indicated on the Drawings, payment for the "Unclassified Structural Excavation", "Common Structural Excavation" or "Rock Structural

Excavation" as the case may be, required below plan grade down to and including an elevation 5 feet (1.5 meters) below drawing grade for any individual footing will be made at a unit price equal to 115 percent of the contract unit bid price. Payment for the excavation from an elevation over 5 feet (1.5 meters) below plan grade down to and including an elevation 10 feet (3.05 meters) below plan grade will be made at a unit price equal to 125 percent of the contract unit bid price for "Unclassified Structural Excavation", "Common Structural Excavation" or "Rock Structural Excavation" as the case may be. No increase in unit price will be allowed for other bid items of the contract and no additional compensation will be allowed for any required cofferdam adjustments made necessary by such lowering of footings. These provisions shall not apply to the lowering of culverts, except when the flow line grade is lowered 1 foot (300 mm) or more below plan grade.

In cases where the extra depths required for any footing or footings exceeds 10 feet (3.05 meters), a supplemental agreement shall be made covering the quantities removed from depths in excess of 10 feet (3.05 meters) below plan grade.

No direct payment will be made for filling or backfilling around structures. Payment for the backfilling and compacting of areas, which were removed as structural excavation shall be included in the unit bid prices for the various classes of structural excavation.

At the end of each estimate period, the Engineer or designated representative shall determine the completed portion of the total work under Standard Specification Item No. 401S "Structural Excavation and Backfill" and payment shall be made accordingly.

Filling or backfilling of areas above the natural ground level or above the limits of street excavation or channel excavation sections shall be considered as Standard Specification Item No. 132S, "Embankment" and payment therefore shall be included in the unit prices bid for the various classes of Standard Specification Item No. 110S, "Street Excavation", Standard Specification Item No. 120S, "Channel Excavation" or Standard Specification Item No. 130S, "Borrow".

Where no channel excavation is provided for at culvert sites and where it is necessary to excavate beyond the limits of structural excavation, as herein described in order that the culvert may function properly, such excavation shall be included with structural excavation as may be indicated on the Drawings.

Payment for all work prescribed under this item shall include full compensation for all excavation and backfill including compaction, all soundings, construction of all cofferdams, all dewatering and for furnishing all materials, labor, equipment, tools, sheathing, bracing, cofferdams, pumps, drills, explosives and incidentals necessary to complete the work, except for specific allowances stated above.

Special materials used or additional excavation made for the Contractor's convenience to expedite the work will not be paid for directly, but shall be included in the unit price bid for this specification item. In addition, if the Contractor's construction methods and equipment creates conditions necessitating usage of special materials or additional excavation, the work and materials will not be paid for directly, but shall be included in the unit price bid for this specification item.

When specified in the contract bid form as separate pay item(s), the item(s) will be paid for at the contract unit price(s) for "Flexible Base", "Lime Stabilized Base" and "Controlled Low Strength Material". The bid prices shall include full compensation for all Work herein, specified,

including the disposal of all material not required in the Work, the furnishing of all material, equipment, tools, labor and incidentals necessary to complete the Work.

Payment will be made under one of the following:

Pay Item No. 401S-A:	Unclassified Structural Excavation, <u>Plan Quantity</u>	Per Cubic Yard, <u>Plan Quantity</u>
Pay Item No. 401S-B:	Common Structural Excavation	Per Cubic Yard.
Pay Item No. 401S-C:	Rock Structural Excavation	Per Cubic Yard.
Pay Item No. 401S-D:	Concrete Base	Per Cubic Yard.
Pay Item No. 401S-E:	Cement Stabilized Backfill	Per Cubic Yard.
Pay Item No. 401S-F:	Flexible Base	Per Cubic Yard.
Pay Item No. 401S-G:	Lime Stabilized Base	Per Square Yard.
Pay Item No. 401S-H:	Controlled Low Strength Material	Per Cubic Yard.
Pay Item No. 401S-I:	Cofferdams, type _____	Per Cubic Yard.
Pay Item No. 401S-J:	Dewatering	Per Cubic Yard.

End

SPECIFIC CROSS REFERENCE MATERIALS
Standard Specification Item 401S, "Structural Excavation and Backfill"

City of Austin Standard Contract Documents
 Designation Description
 Section 00700 General Conditions
 Section 01550 Public Safety and Convenience

City of Austin Utilities Criteria Manual
 Designation Description
 Section 5.2.0 Permit Information and Format

City of Austin Standard Specification Items
 Designation Description
 Item No. 110S Street Excavation
 Item No. 111S Excavation
 Item No. 120S Channel Excavation
 Item No. 130S Borrow
 Item No. 132S Embankment
 Item No. 202S Hydrated Lime and Lime Slurry
 Item No. 203S Lime Treatment for Materials in Place
 Item No. 210S Flexible Base
 Item No. 302S Aggregates for Surface Treatments
 Item No. 402S Controlled Low Strength Material
 Item No. 403S Concrete for Structures
 Item No.509S Excavation Safety Systems
 Item No. 610S Preservation of Trees and Other Vegetation

Texas Department of Transportation: Departmental Material Specifications
 Designation Description
 DMS-4640 Chemical Admixtures for Concrete

American Society for Testing and Materials, ASTM	
Designation	Description
ASTM C 33	Specification For Concrete Aggregates
Texas Department of Transportation: Manual of Testing Procedures	
Designation	Description
Tex-114-E	Laboratory Compaction Characteristics & Moisture-Density Relationship of Subgrade & Embankment Soil
Tex-120-E	Soil-Cement Testing

RELATED CROSS REFERENCE MATERIALS
Standard Specification Item 401S, "Structural Excavation and Backfill"

Texas Department of Transportation: Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges	
Designation	Description
Item 110	Excavation
Item 132	Embankment
Item 400	Excavation and Backfill for Structures
Item 401	Flowable Backfill
Item 402	Trench Excavation Protection
Item 403	Temporary Special Shoring
Item 421	Hydraulic Cement Concrete

Item No. 403S
Concrete for Structures

403S.1 Description

This item shall govern quality, storage, handling, proportioning and mixing of materials for hydraulic cement concrete construction of buildings, bridges, culverts, slabs, prestressed concrete and incidental appurtenances.

This specification is applicable for projects or work involving either inch-pound or SI units. Within the text, the inch-pound units are given preference followed by SI units shown within parentheses.

403S.2 Submittals

The submittal requirements of this specification item may include:

- A. Mix design option(s) of the class of concrete required on the project,
- B. The supplier of the concrete mix design(s) and type of mixing equipment, and
- C. Type of admixtures to be used with the concrete mixes.

403S.3 Materials

Concrete shall be composed of hydraulic cement or hydraulic cement and supplementary cementing materials, water, aggregates (fine and coarse), and admixtures proportioned and mixed as hereinafter provided to achieve specified results.

A. Cementitious Materials

Hydraulic cement shall conform to ASTM C 150, Type I (General Purpose), Type II (General Purpose with Moderate Sulfate Resistance) and Type III (High Early Strength). Type I shall be used when none is specified or indicated on the drawings. Type I and Type III cements shall not be used when a Type II cement is specified or indicated on the drawings. Type III cement may be used in lieu of a Type I cement, when the anticipated air temperature for the succeeding 12 hours will not exceed 60°F (15.6°C). A Type III cement shall only be used in precast concrete or when otherwise specified or allowed. All cement shall be of the same type and from the same source for a monolithic placement.

Unless otherwise specified the cementitious material content shall be limited to no more than 700 lbs. per cubic yard (417 kg per cubic meter). When supplementary cementing materials are used, cement is defined as "cement plus supplementary cementing material." Supplementary cementing materials include fly ash (DMS 4610), ultra-fine fly ash (DMS-4610), ground granulated blast furnace slag grade 100 or 120 (DMS-4620), silica fume (DMS-4630) and metakaolin (DMS-4635).

Supplementary cementing materials shall not be used when white hydraulic cement is specified.

Class C flyash shall not be used in sulfate-resistant concrete.

Hydraulic cement manufactured in a cement kiln fueled by hazardous waste shall be considered as an approved product if the production facility is authorized to operate under regulation of the Texas Commission on Environmental Quality (TCEQ) and the U. S.

Environmental Protection Agency (EPA). Supplier shall provide current TNRCC and EPA authorizations to operate the facility.

When sulfate-resistant concrete is required for a project, mix design options 1, 2, 3 or 4 presented in Section 403S.8, "Mix Design Options" shall be used to develop appropriate mix design utilizing Type I/II, II, V, IP or IS cement.

B. Mixing Water

Water for use in concrete and for curing shall be potable water free of oils, acids, organic matter or other deleterious substances and shall not contain more than 1,000 parts per million of chlorides as Cl or sulfates as SO₄.

Water from the City of Austin will not require testing. Contractor may request approval of water from other sources. Contractor shall arrange for samples to be taken from the source and tested at his expense. When water from other sources is proposed, test reports shall be provided that indicates compliance with Table 1 before use.

Table 1: Chemical Limits for Mix Water		
Contaminant	Test Method	Maximum Concentration (ppm)
Chloride (CL)	ASTM D-512	
Prestressed concrete		500
Bridge decks & superstructure		500
All other concrete		1,000
Sulfate (SO ₄)	ASTM D-516	1,000
Alkalies (NA ₂ O + 0.658 K ₂ O)	ASTM D-4191 & D-4192	600
Total Solids	AASHTO T-26	50,000

Water that has an adverse effect on the air-entraining agent or any other chemical admixture or on strength or time of set of the concrete shall not be used. Water used in white Portland cement concrete shall be free from iron and other impurities, which may cause staining, or discoloration.

C Coarse Aggregate

Coarse aggregate shall consist of durable particles of crushed or uncrushed gravel, crushed blast furnace slag, crushed stone or combinations thereof; free from frozen material or injurious amounts of salt, alkali, vegetable matter or other objectionable material either free or as an adherent coating. When white hydraulic cement is specified, the coarse aggregates used in the concrete shall be light colored. Quality shall be reasonably uniform throughout.

The coarse aggregate from each source shall not contain more than 0.25 percent by weight of clay lumps, nor more than 1.0 percent by weight of shale nor more than 5 percent by weight of laminated and/or friable particles when tested in accordance with TXDOT Test Method TEX-413-A. The coarse aggregate from each source shall have a wear of not more than 40 percent when tested in accordance with TXDOT Test Method TEX-410-A.

Unless otherwise indicated on the drawings, the coarse aggregate from each source shall be subjected to 5 cycles of the soundness test conforming to TXDOT Test Method TEX-411-A. The loss shall not be greater than 12 percent when sodium sulfate is used or 18 percent when magnesium sulfate is used.

Coarse aggregate shall be washed. The Loss by Decantation (TXDOT Test Method TEX-406-A), plus allowable weight of clay lumps, shall not exceed 1 percent or the value indicated on the drawings or in the project manual, whichever is less. If material finer than the # 200

(75 micrometer) sieve is definitely established to be dust of fracture of aggregates made primarily from crushing of stone, essentially free from clay or shale as established by Part III of TXDOT Test Method TEX-406-A, the percent may be increased to 1.5. When crushed limestone coarse aggregate is used in concrete pavements, the decant may exceed 1% but not more than 3% if the material finer than the # 200 (75 micrometer) sieve is determined to be at least 67% calcium carbonate in accordance with TxDoT Test Method Tex-406-A, Part III.

The coarse aggregate factor may not be more than 0.82; however, when voids in the coarse aggregate exceed 48 percent of the total rodded volume, the coarse aggregate factor shall not exceed 0.85. The coarse aggregate factor may not be less than 0.68 except for a Class I machine extruded mix that shall not have a coarse aggregate factor lower than 0.61.

When exposed aggregate surfaces are required, the coarse aggregate shall consist of particles with at least 40 percent crushed faces. Uncrushed gravel, polished aggregates and clear resilient coatings are not acceptable for exposed aggregate finishes.

When tested by approved methods, the coarse aggregate including combinations of aggregates when used, shall conform to the grading requirements shown in Table 2.

Grade	Nom. Size	2-1/2" (62.5mm)	2" (50mm)	1 1/2" (37.5mm)	1" (25mm)	3/4" (19mm)	1/2" (12.5mm)	3/8" (9.5mm)	No. 4 (4.75mm)	No. 8 (2.36mm)
1	2" (50 mm)	100	80-100	50-85		20-40			0-5	
2 (467)*	1 1/2"(37.5 mm)		100	95-100		35-70		10-30	0-5	
3	1" (50 mm)		100	95-100		60-90	25-60		0-5	
4 (57)*	1" (50 mm)			100	95-100		25-60		0-10	0-5
5 (67)*	3/4" (19 mm)				100	90-100		20-55	0-10	0-5
6 (7)*	1/2" (12.5 mm)					100	90-100	40-70	0-15	0-5
7	3/8"(9.5 mm)						100	70-95	0-25	
8	3/8" (9.5 mm)						100	95-100	20-65	0-10

Notes:

1. Recycled crushed concrete fine aggregate shall be limited to a maximum of 20% of the fine aggregate.
2. The use of recycled crushed hydraulic cement concrete as a coarse aggregate shall be limited to Concrete Classes A, B and D (see Table 5).

D. Fine Aggregate

Fine aggregate shall be washed and consist of clean, hard, durable and uncoated particles of natural or manufactured sand or a combination thereof, with or without a mineral filler. When white hydraulic cement is specified, the fine aggregates used in the concrete shall be light colored. Quality shall be reasonably uniform throughout It shall be free from frozen material or injurious amounts of salt, alkali, vegetable matter or other objectionable material and it shall not contain more than 0.5 percent by weight of clay lumps in accordance with TEX-413-A. When subjected to color test for organic impurities per TXDOT Test Method TEX-408-A, it shall not show a color darker than standard.

Unless indicated otherwise on the drawings the acid insoluble residue of fine aggregate used in slab concrete subject to direct traffic shall not be less than 60 percent by weight (mass) when tested conforming to TXDOT Test Method TEX-612-J.

Unless indicated otherwise on the Drawings, fine aggregate shall be blended, when necessary, to meet the acid insoluble residue requirement.

When blending the following equation shall be used:

$$\text{Acid Insoluble (\%)} = \frac{(A1)(P1) + (A2)(P2)}{100}$$

Where:

- A1 = acid insoluble (%) of aggregate 1,
- A2 = acid insoluble (%) of aggregate 2,
- P1 = % by weight of A1 of the fine aggregate blend, and
- P2 = % by weight of A2 of the fine aggregate blend.

When tested in accordance with TxDOT Test Method Tex-401-A, the fine aggregate, including mineral filler and combinations of aggregates, when used, shall conform to the grading requirements shown in Table 3.

Table 3: Fine Aggregate Gradation Chart¹ (Grade 1 - Percent Passing)							
3/8 (9.5 mm)	No. 4 (4.75 mm)	No. 8 (2.36 mm)	No. 16 (1.18mm)	No. 30 (600 μm)	No. 50 (300 μm)	No. 100 (150 μm)	No. 200 (75 μm)
100	95-100	80-100	50-85	25-65	10-35 ¹	0-10	0-3 ²

Notes:

1. Recycled crushed concrete fine aggregate shall be limited to a maximum of 20% of the fine aggregate.
2. The use of recycled crushed hydraulic cement concrete as a fine aggregate shall be limited to Concrete Classes A, B and D (see Table 5).
3. 6 to 35 when sand equivalent value is greater than 85.
4. 0 to 6 for manufactured sand.

Sand equivalent per TXDOT Test Method TEX-203-F shall not be less than 80 nor less than otherwise indicated on the drawings, whichever is greater.

The fineness modulus will be determined by adding the percentages by weight retained on sieve Nos. 4, 8, 16, 30, 50 and 100 (4.75 mm, 2.36 mm, 1.18mm, 600 μm, 300 μm, and 150 μm) and dividing the sum of the six sieves by 100. For all classes of concrete except K (see Table 5), the fineness modulus shall be between 2.30 and 3.10. For Class K concrete, the fineness modulus shall be between 2.40 and 2.90, unless indicated otherwise on the Drawings.

E. Mineral Filler

Mineral filler shall consist of stone dust, clean crushed sand or other approved inert material. When tested in accordance with TxDOT Test Method Tex-401-A, it shall conform to the following gradation:

Passing the No. 30 (600 μm) Sieve	100 percent
Passing the No. 200 (75 μm) Sieve	65 to 100 percent

F. Mortar and Grout

Unless otherwise specified, indicated on the drawings or approved by the Engineer or designated representative mortar and grout shall consist of 1 part hydraulic cement, 2 parts finely graded sand and enough water to make the mixture plastic. When required to prevent color difference, white cement shall be added to produce color required. When

required by the Engineer or designated representative, approved latex adhesive may be added to the mortar. Mortar shall be provided with a consistency such that the mortar can be easily handled and spread by trowel. Grout shall be provided of a consistency that will flow into and completely fill all voids.

G. Admixtures

All chemical admixtures including water reducing, plasticizers and air entrainment shall conform to TxDOT DMS-4640, "Chemical Admixtures for Concrete". Calcium chloride-based admixtures shall not be approved. Admixtures shall be included in the prequalified concrete admixtures list maintained by TxDOT's Construction Division. High-range water-reducing admixtures (TxDOT Type F or G) and accelerating admixtures (TxDOT Type C or E) shall not be used in bridge deck concrete.

H. Air Entrainment

Unless indicated otherwise on the drawings, all concrete classes with the exception of Class B shall be air-entrained in accordance with Table 8. If the air content is more than 1-1/2 percentage points below or 3 percentage points above the required air, the load of concrete will be rejected. If the air content is more than 1-1/2 but less than 3 percentage points above the required air, the concrete may be accepted based on strength test results.

403S.4 Storage of Materials

A. Cement, Supplementary Cementing Materials and Mineral Filler

All cement, supplementary cementing materials and mineral filler shall be stored in separate and well ventilated, weatherproof buildings or approved bins, which will protect the material from dampness or absorption of moisture. Storage facilities shall be easily accessible and each shipment of packaged cement shall be kept separated to provide for identification and inspection. The Engineer or designated representative may permit small quantities of sacked cement to be stored in the open for a maximum of 48 hours on a raised platform and under waterproof covering.

B. Aggregates

The method of handling and storing concrete aggregates shall prevent contamination with foreign materials. If the aggregates are stored on the ground, the sites for the stockpiles shall be clear of all vegetation and shall be level. Aggregates shall be stockpiled in sizes to facilitate blending. If the aggregate is not stockpiled on a hard, non-contaminant base, the bottom 6-inch (150 mm) layer of the stockpile shall not be used without recleaning the aggregate.

When conditions require the use of 2 or more grades of coarse aggregates, separate stockpiles shall be maintained to prevent intermixing. Where space is limited, stockpiles shall be separated by walls or other appropriate barriers.

Aggregate shall be stockpiled and protected from the weather a minimum of 24 hours prior to use to minimize free moisture content. When stockpiles are too large to protect from the weather, accurate and continuous means acceptable to the Engineer or designated representative shall be provided to monitor aggregate temperature and moisture. Aggregates shall be stockpiled and handled such that segregation and contamination are minimized.

The stockpiles shall be sprinkled to control moisture and temperature as necessary. A reasonably uniform moisture content shall be maintained in aggregate stockpiles.

C. Admixtures

Admixtures shall be stored in accordance with manufacturer's recommendations and shall be protected against freezing.

D. Hot Weather Concrete Mixes

Ice may be used during hot weather concrete placement (Section 13 of Standard Specification Item No. 410S, "Concrete Structures") to lower the concrete temperature; however, the Contractor shall furnish a mix design acceptable to the Engineer or designated representative for class of concrete specified. The addition of ice shall not exceed 50% of the total mix water weight.

403S.5 Measurement of Materials

Water shall be accurately metered. Fine and coarse aggregates, mineral filler, bulk cement and fly ash shall be weighed separately. Allowances shall be made in the water volume and aggregate weights during batching for moisture content of aggregates and admixtures. Volumetric and weight measuring devices shall be acceptable to the Engineer or designated representative. Measurement of materials in non-volumetric and volumetric mixers shall conform to Section 421.4.D of TxDot Specification Item 421, "Hydraulic Cement Concrete".

Batch weighing of sacked cement is not required; however, bags, individually and entire shipments, may not vary by more than 3 percent from the specified weight of 94 pounds (42.6 kilograms) per bag. The average bag weight of a shipment shall be determined by weighing 50 bags taken at random.

403S.6 Mix Design

The Contractor shall furnish a mix design acceptable to the Engineer or designated representative for the class of concrete required in accordance with Table 5. The mix shall be designed by a qualified commercial laboratory and signed/sealed by a registered Professional Engineer, licensed in the state of Texas to conform with requirements contained herein, to ACI 211.1 or TXDOT Bulletin C-11 (and supplements thereto). The maximum water-to-cementitious material ratio identified in Table 5 for specific classes of concrete shall not be exceeded.

A higher-strength class of concrete with equal or lower water-to-cementitious-material ratio may be substituted for the specified class of concrete.

The mix design shall be over-designed in accordance with Table 5 in order to account for production variability and to ensure minimum compressive strength requirements are met.

Allowable mix design options are presented in Section 403S.8.

The Contractor shall perform, at his own expense, the work required to substantiate the design, including testing of strength specimens. Complete concrete design data shall be submitted to the Engineer or designated representative for approval. The mix design will be valid for a period of one (1) year provided that there are no changes to the component materials.

When there are changes in aggregates or in type, brand or source of cement, supplementary cementing material or chemical admixtures, the mix shall be evaluated as a new mix design. A change in vendor does not necessarily constitute a change in materials or source. When only the brand or source of cement is changed and there is a prior record of satisfactory performance of the cement with the ingredients, the submittal of new trial batches may be waived by the Engineer or designated representative.

At the end of one (1) year, a previously approved mix may be resubmitted for approval if it can be shown that no substantial change in the component materials has occurred and that test results confirming the adequacy of the mix designs have been acquired during the previous year. The resubmittal analysis must be reviewed, signed and sealed by a registered Professional Engineer, licensed in the state of Texas. This resubmittal shall include a reanalysis of specific gravity, absorption, fineness modulus, sand equivalent, soundness, wear and unit weights of the aggregates. Provided that the fineness modulus did not deviate by more than 0.20 or that the re-proportioned total mixing water, aggregate and cement (or cement plus fly ash) are within 1, 2, and 3 percent, respectively, of pre-approved quantities, a one-year extension on the approval of the mix may be granted by the Engineer or designated representative. Updated cement, fly ash, and admixture certifications shall accompany the resubmittal.

Approved admixtures that are included in the prequalified concrete admixtures list maintained by TxDot’s Construction Division may be used with all classes of concrete at the option of the Contractor provided that specific requirements of the governing concrete structure specification are met. Water reducing and retarding agents shall be required for hot weather, large mass, and continuous slab placements. Air entraining agents may be used in all mixes but must be used in the classes indicated on Table 5. Unless approved by the Engineer or designated representative, mix designs shall not exceed air contents for extreme exposure conditions as recommended by ACI 211.1 for the various aggregate grades.

403S.7 Consistency and Quality of Concrete

Concrete shall be workable, cohesive, possess satisfactory finishing qualities and of stiffest consistency that can be placed and vibrated into a homogeneous mass within slump requirements specified in Table 4 without the development of segregation or honeycombing. No concrete will be permitted with a slump in excess of the maximums shown unless water-reducing admixtures have been previously approved. Concrete that exceeds the maximum acceptable placement slump at time of delivery will be rejected. Slump values shall be conducted in accordance with TXDOT Test Method TEX-415-A.

Consistency and quality of concrete should allow efficient placement and completion of finishing operations before initial set. Re-tempering (i.e. addition of water and reworking concrete after initial set) shall not be allowed. When field conditions are such that additional moisture is needed for final concrete surface finishing operation, the required water shall be applied to surface by fog spray only and shall be held to a minimum. Excessive bleeding shall be avoided and in no case will it be permissible to expedite finishing and drying by sprinkling the surface with cement powder.

Table 4: Slump Requirements		
Type of Construction	Slump¹, inches (mm)	
	Maximum	Minimum
Cased Drilled Shafts	4 (100)	3 (75)

Reinforced Foundation Caissons and Footings	3 (75)	1 (25)
Reinforced Footings and Substructure Walls	3 (75)	1 (25)
Uncased Drilled Shafts	6 (150)	5 (125)
Thin-walled Sections; 9 inches (225 mm) or less	6 ½ (165)	4 (100)
Prestressed Concrete Members ¹	6 ½ (165)	4 (100)
Precast Drainage Structures	6 (150)	4 (100)
Wall Sections over 9 inches (225 mm)	5 (125)	3 (75)
Reinforced Building Slabs, Beams, Columns and Walls	4 (100)	1 (25)
Bridge Decks	4 (100)	2 (50)
Pavements, Fixed-form	6 ½ (165)	4 (100)
Pavements, Slip-form	3 (75)	1-½ (37.5)
Sidewalks, Driveways and Slabs on Ground	4 (100)	2 (50)
Curb & Gutter, Hand-vibrated	3 (75)	1 (25)
Curb & Gutter, Hand-tamped or spaded	4 (100)	2 (50)
Curb & Gutter, Slip-form/extrusion machine	2 (50)	½ (12.5)
Heavy Mass Construction	2 (50)	1 (25)
High Strength Concrete	4 (100)	3 (75)
Riprap and Other Miscellaneous Concrete	6 (150)	1 (25)
Under Water or Seal Concrete	8 ½ (213)	6 (150)

1. Slump values when a high range water reducer (HRWR) is not used.
2. When a high range water reducer (HRWR) is used, maximum acceptable placement slump will be 9 in (225 mm)

During progress of the work, the Engineer or designated representative shall cast test cylinders as a check on compressive strength of concrete actually placed. The Engineer or designated representative may also perform slump tests, entrained air tests and temperature checks to ensure compliance with specifications.

Proportioning of all material components shall be checked prior to discharging. Excluding mortar material for pre-coating of the mixer drum [see section 403S.8.B and adjustment for moisture content of admixtures and aggregates, material components shall fall within the range of + 1% for water, + 2% for aggregates, + 3% for cement, +2% for fly ash and within manufacturer recommended dosage rates for admixtures except that air entrainment shall be within + 1-1/2 percentage points of the mix design requirements.

Unless otherwise specified or indicated on the drawings, concrete mix temperature shall not exceed 90°F (32°C) except in mixes with high range water reducers where a maximum mix temperature of 100°F (38°C) will be allowed. Cooling an otherwise acceptable mix by addition of water or ice during agitation will not be allowed.

Test cylinders will be required for small placements such as manholes, inlets, culverts, wing walls, etc. The Engineer or designated representative may vary the number of tests to a minimum of 1 for each 25 cubic yards (1 for each 19 cubic meters) placed over a several day period.

Test cylinders shall be required for each monolithic placement of bridge decks or superstructures, top slabs of direct traffic culverts, cased drilled shafts, structural beams and as otherwise directed by Engineer or designated representative for design strength confirmation or early form removal. Test cylinders made for early form removal or for

consideration of use of structure will be at Contractor's expense, except when required by Engineer or designated representative.

A strength test shall be defined as the average breaking strength of 2 cylinders. A minimum of four test cylinders shall be prepared; two each to be tested at 7 and 28 days. Specimens will be tested conforming to TXDOT Test Method TEX-418-A. If required strength or consistency of class of concrete being produced cannot be secured with minimum cementitious material specified or without exceeding maximum water/cementitious material ratio, Contractor will be required to furnish different aggregates, use a water reducing agent, an air entraining agent or increase the cement content in order to provide concrete meeting these specifications.

Slump tests will be performed in accordance with TxDOT Test Method Tex-415-A. Entrained air tests will be performed in accordance with TxDOT Test Method Tex-416-A.

Test specimens shall be cured using the same methods and under the same conditions as the concrete represented. Design strength cylinders shall be cured conforming to TXDOT Bulletin C-11 (and supplements thereto).

When control of concrete quality is by 28-day compressive tests, job control testing will be by 7-day compressive strength tests. The minimum strength requirement for seven (7) day test will be 70 percent of the specified minimum 28-day compressive strength. If the required 7-day strength is not secured with the quantity of cement specified in Table 4, changes in the mix design shall be made and resubmitted for approval. For an occasional failure of the seven-day compressive test, the concrete may be tested at 28 days for final evaluation.

Class	Cement Sks Per CY	Minimum Strength, psi (MPa)		Maximum W/C Ratio ¹	Coarse Aggr. Grade ^{2,3,4}	Air Entrain.
		28 Days	7 Days			
A	5.0 (280 kg/m ³)	3000 (20.6)	2100 (14.5)	0.6	1,2,3,4, 8	Yes
B	4.0 (225 kg/m ³)	2000 (13.8)	1400 (9.7)	0.6	2,3,4,5,6,7	No
C ⁵	6.0 (335 kg/m ³)	3600(24.8)	2520 (17.4)	0.45	1,2,3,4,5,6	Yes
D	4.5 (252 kg/m ³)	2500 (17.2)	1750 (12.1)	0.6	2,3,4,5,6,7	No
H ⁵	6.0 (335 kg/m ³)	As indicated	As Indicated	0.45	3,4,5,6	Yes
I	5.5 (308 kg/m ³)	3500 (24.1)	2450 (16.9)	0.45	2,3,4,5	Yes
J	2.0 (112 kg/m ³)	800 (5.5)	560 (3.9)	N/A	2,3,4,5	No
S ⁵	6.0 (335 kg/m ³)	4000 (27.6)	2800 (19.3)	0.45	2,3,4,5	Yes

Notes:

1. Maximum water-cement or water-cementitious ratio by weight
2. Unless otherwise allowed, Grade 1 coarse aggregate shall only be used in massive foundations with 4-in (100-mm) minimum clear spacing between reinforcing steel bars.
3. Grade 1 coarse aggregate grading shall not be used in drilled shafts.
4. Unless otherwise allowed, Grade 8 coarse aggregate shall be used in extruded curbs.
5. Structural concrete classes.
6. When Type II cement is used in Class C, S or A concrete, the 7-day compressive strength requirement will be 2310 psi (15.9 MPa) for Class C, 2570 psi (17.7 MPa) for Class S and 1925 psi (13.3 MPa) for Class A minimum.

Table 6: Over Design Required to Meet Compressive Strength Requirements¹

Number Of Tests ^{2,3}	Standard Deviation, psi (MPa)				
	300 (2.06)	400 (2.75)	500 (3.44)	600 (4.13)	700 (4.82)
15	470 (3.24)	620 (4.27)	850 (5.85)	1,120 (7.71)	1,390 (9.57)
20	430 (2.96)	580 (3.99)	760 (5.23)	1,010 (6.95)	1,260 (8.67)
30 or more	400 (2.75)	530 (3.65)	670 (4.61)	900 (6.20)	1,130 (7.78)

Notes:

1. When designing the mix, add the tabulated amounts to the minimum design strength in Table 5. Maximum water-cement or water-cementitious ratio by weight
2. Number of tests of a concrete mixture used to estimate the standard deviation of a concrete production facility. Test of another mix within 1,000 psi (6.88 MPa) of the specified strength may be used.
3. If less than 15 prior tests are available, the overdesign should be 1,000 psi (6.88 MPa) for specified strength less than 3,000 psi (20.65 MPa), 1,200 psi (8.26 MPa) for specified strengths from 3,000 to 5,000 psi (20.65 to 34.42 MPa) and 1,400 psi (9.64 MPa) for specified strengths greater than 5,000 psi (34.42 MPa).

Table 7: Expected Usage of Concrete Classes

Class	General Usage
A	Inlets, manholes, curb, gutter, curb & gutter, concrete retards, sidewalks, driveways, backup walls and anchors
B	Riprap, small roadside signs and anchors
C ⁵	Drilled shafts, bridge substructure, bridge railing, culverts except top slab of direct traffic culverts, headwalls, wing walls, approach slabs, and cast-in-place concrete traffic barrier
D	Riprap
H ⁵	Prestressed concrete beams, boxes, piling and precast concrete traffic barrier
J	Utility trench repair
S ⁵	Bridge slabs and top slabs of direct traffic culverts

Table 8: Air Entrainment¹

Nominal Maximum Aggregate Size In (mm)	% Air Entrainment	
	Moderate Exposure	Severe Exposure
3/8 (9.5)- Grades 7 & 8	6	7-1/2
1/2 (12.5)- Grades 6	5-1/2	7
3/4 (19)- Grades 5	5	6
1 (25)- Grades 4	4-1/2	6
1-1/2 (37.5)- Grades 2 & 3	4-1/2	5-1/2
2 (50)- Grades 2	4	5

1. For specified concrete strengths above 5,000 psi (34.42 MPa) a reduction of 1 percentage point is allowed.

403S.8 Mix Design Options

For the structural concretes identified in Table 5 (Classes C, H and S) and any other class of concrete designed using more than 520 lbs. of cementitious material per cubic yard (310 kgs per cubic meter), one of the mix design options presented below shall be used.

For the non-structural concretes identified in Table 5 (Classes A, B, D and I) and any other class of concrete designed using less than 520 lbs. of cementitious material per cubic yard (310 kgs per cubic meter), one of the mix design options presented below will be used, except that Class C fly ash may be used instead of Class F fly ash for Options 1, 3 and 4 unless a sulfate-resistant concrete is required.

- A. Option 1: Twenty (20) to thirty-five (35) percent of the cement may be replaced with Class F fly ash.
- B. Option 2: Thirty-five (35) to fifty (50) percent of the cement may be replaced with ground granulated blast-furnace slag.
- C. Option 3: Thirty-five (35) to fifty (50) percent of the cement may be replaced with a combination of Class F fly ash, ground granulated blast-furnace slag or silica fume. The combination may not include more than thirty-five (35) percent fly ash and no more than ten (10) percent silica fume.
- D. Option 4: Type IP or Type IS will be used and up to ten (10) percent of the cement may be replaced with Class F fly ash, ground granulated blast-furnace slag or silica fume.
- E. Option 5: Thirty-five (35) to fifty (50) percent of the cement may be replaced with a combination of Class C fly ash and at least six (6) percent of silica fume, ultra fine fly ash or metakaolin. The combination may not include more than thirty-five (35) percent fly ash and no more than ten (10) percent silica fume.
- F. Option 6: A lithium nitrate admixture will be added at a minimum dosage of 0.55 gal. Of thirty (30) percent lithium nitrate solution per pound of alkalis present in the hydraulic cement.
- G. Option 7: When hydraulic cement only is used in the design, the total alkali contribution from the cement in the concrete does not exceed 4.0 lbs. Per cubic yard, when calculated as follows:

$$\text{alkali (lbs. per CY)} = .01 (\text{lbs cement/CY}) (\% \text{ Na}_2\text{O equivalent in cement})$$

where (% Na₂O equivalent in cement) is assumed to be the maximum cement alkali content reported on the cement mill certificate.
- H. Option 8: When there are deviations from Options 1 through 7, the following shall be performed:
 1. Conduct tests on both coarse and fine aggregate separately in accordance with ASTM C-1260, using 440 g of the proposed cementitious in the same proportions of hydraulic cement to supplementary cementing material to be used in the mix.
 2. Prior to use of the mix, a certified test report signed and sealed by a Professional Engineer, licensed in the state of Texas shall be submitted that demonstrates that ASTM C 1260 test results for each aggregate do not exceed 0.10 percent expansion.

403S.9 Mixing and Mixing Equipment

All equipment, tools and machinery used for hauling materials and performing any part of the work shall be maintained in such condition to insure completion of the work without excessive delays for repairs and replacement. Mixing shall be done in a mixer of approved type and size that will produce uniform distribution of material throughout the mass and shall be capable of producing concrete meeting requirements of ASTM C 94, Ready-mixed Concrete and these specifications. Mixing equipment shall be capable of producing sufficient concrete to provide required quantities. Entire contents of the drum shall be discharged before any materials are placed therein for a succeeding batch. Improperly mixed concrete shall not be placed in a structure. For all mixers an adequate water supply and an accurate method of measuring the water shall be provided.

The mixer may be batched by either volumetric or weight sensing equipment and shall be equipped with a suitable timing device that will lock the discharging mechanism and signal when specified time of mixing has elapsed.

A. Proportioning and Mixing Equipment

For all miscellaneous concrete placements, a mobile, continuous, volumetric mixer or a volumetric or weight batch mixer of the rotating paddle type may be used.

When approved by Engineer or designated representative in writing or when specified for use in other items, these mixers may be used for other types of concrete construction, including structural concrete, if the number of mixers furnished will supply the amount of concrete required for the particular operation in question.

These mixers shall be designed to receive all the concrete ingredients, including admixtures, required by the mix design in a continuous uniform rate and mix them to the required consistency before discharging.

For continuous volumetric mixers, the materials delivered during a revolution of the driving mechanism or in a selected interval, will be considered a batch and the proportion of each ingredient will be calculated in the same manner as for a batch type plant.

Mixing time shall conform to recommendations of manufacturer of mixer unless otherwise directed by Engineer or designated representative.

B. Ready-mixed Concrete

Use of ready-mixed concrete will be permitted provided the batching plant and mixer trucks meet quality requirements specified herein. When ready-mixed concrete is used, additional mortar (1 sack cement, 3 parts sand and sufficient water) shall be added to each batch to coat the mixer drum. Ready-mixed concrete, batching plant and mixer truck operation shall include the following:

1. A ticket system will be used that includes a copy for the Inspector. Ticket will have machine stamped time/date of concrete batch, a mix design designation, weight of cement, fly ash, sand and aggregates; exact nomenclature and written quantities of admixtures and water. Any item missing or incomplete on ticket may be cause for rejection of concrete.
2. Sufficient trucks will be available to support continuous placements. The Contractor will satisfy the Engineer or designated representative that adequate standby trucks are available to support monolithic concrete placement requirements.
3. A portion of mixing water required by the mix design to produce the specified slump may be withheld and added at the job site, but only with permission of the Engineer

or designated representative and under the Inspector's observation. When water is added under these conditions, the concrete batch will be thoroughly mixed before any slump or strength samples are taken. Additional cement shall not be added at the job site to otherwise unacceptable mixes.

4. A metal plate(s) shall be attached in a prominent place on each truck mixer plainly showing the various uses for which it was designed. The data shall include the drum's speed of rotation for mixing and for agitating and the capacity for complete mixing and/or agitating only. A copy of the manufacturer's design, showing dimensions of blades, shall be available for inspection at the plant at all times. Accumulations of hardened concrete shall be removed to the satisfaction of the Engineer or designated representative.
5. The loading of the transit mixers shall not exceed capacity as shown on the manufacturer's plate attached to the mixer or 63 percent of the drum volume, whichever is the lesser volume. The loading of transit mixers to the extent of causing spill-out enroute to delivery will not be acceptable. Consistent spillage will be cause for disqualification of a supplier.
6. Excess concrete remaining in the drum after delivery and wash water after delivery shall not be dumped on the project site unless approval of the dump location is first secured from the Engineer or designated representative.

C. Volumetric Batching

Use of volumetric batched concrete will be permitted provided the batching and continuous mixing operations conform to ASTM C 685, "Concrete Made By Volumetric Batching and Continuous Mixing". This type concrete shall be made from materials continuously batched by volume, mixed in a continuous mixer and delivered to the site in a freshly mixed and unhardened state. Tests and criteria for batching accuracy and mixing efficiency shall be as specified in ASTM C 685.

1. A ticket system will be used that includes a copy for the Inspector. The ticket will have machine stamped time/date of concrete batch, a mix design designation, weight of cement, fly ash, sand and aggregates; exact nomenclature and written quantities of admixtures and water. Any item missing or incomplete on ticket may be cause for rejection of concrete.
2. Each batching or mixing unit, or both, shall carry in a prominent place a metal plate or plates on which are plainly marked the gross volume of the unit in terms of mixed concrete, discharge speed and the weight-calibrated constant of the machine in terms of a revolution counter or other output indicator. The mixer shall produce a thoroughly mixed and uniform concrete.
3. The batcher-mixer unit shall contain in separate compartments all the necessary ingredients needed for the manufacture of concrete. The unit shall be equipped with calibrated proportioning devices to vary the mix proportions and it shall produce concrete as required by the Work and ASTM C 685.

D. Truck-mixed Concrete

The concrete shall be mixed in a truck mixer from 70 to 100 revolutions at the mixing speed designated by the manufacturer that will produce a uniform concrete mix. The concrete shall be delivered to the project in a thoroughly mixed and uniform mass and shall be discharged with a satisfactory degree of uniformity. Additional mixing at the job site, at the mixing speed designated by the manufacturer, may be allowed by the

Engineer or designated representative as long as the concrete is discharged before the drum has revolved a total of 300 revolutions after the introduction of the mixing water to the cement and the aggregates.

Re-tempering or adding concrete chemical admixtures is only permitted at the job site when concrete is delivered in a truck mixer. Water shall not be added after introduction of mixing water at the batch plant except on arrival at the job site with approval of the Engineer or designated representative, in order to adjust the slump of the concrete. When this water is added, the mix design water-cementitious-material ratio shall not be exceeded. The drum or blades shall be turned at least 30 additional revolutions at mixing speed to ensure thorough and uniform mixing of the concrete. Water or chemical admixtures shall not be added to the batch after any concrete has been discharged.

When the concrete contains silica fume, mixing times and batching operations shall be adjusted as necessary to ensure that the material is completely and uniformly dispersed in the mix. The dispersion of the silica fume within the mix shall be verified in trial batches.

E. Hand-mixed Concrete

Hand mixing of concrete may be permitted for small placements or in case of an emergency and then only on authorization of the Engineer or designated representative. Hand-mixed batches shall not exceed a 4 cubic foot (0.113 cubic meters) batch in volume. Material volume ratios shall not be leaner than 1 part cement, 2 parts large aggregate, 1 part fine aggregate and enough water to produce a consistent mix with a slump not to exceed 4 inches (100 mm). Admixtures shall not be used unless specifically approved by the Engineer or designated representative.

403S.10 Excavation, Placing of Concrete, Finishing, Curing and Backfill

Excavation, placing of concrete, finishing, curing and backfill shall conform to Standard Specification Item No. 401S, "Structural Excavation and Backfill", Standard Specification Item No. 410S, "Concrete Structures" and Standard Specification Item No. 411S, "Surface Finishes for Concrete".

403S.11 Measurement

Where measurement of concrete for a structure is not provided by another governing pay item, measurement shall be made under this specification in accordance with the following.

The quantities of concrete of the various classifications which constitute the completed and accepted structure or structures in place will be measured by the cubic yard (cubic meters: 1 cubic meter is equal to 1.308 cubic yards), each, ~~square Foot~~ square yard (square meter: 1 square yard equals 0.836 square meters) or linear foot as indicated in the Contract Documents. Measurement will be as follows:

A. General

1. Measurement based on dimensions shall be for the completed structure as measured in place. However, field-measured dimensions shall not exceed those indicated on the drawings or as may have been directed by the Engineer or designated representative in writing.

2. No deductions shall be made for chamfers less than 2 inches (50 mm) in depth, embedded portions of structural steel, reinforcing steel, nuts, bolts, conduits less than 5 inches (125 mm) in diameter, pre/post tensioning tendons, keys, water stops, weep holes and expansion joints 2 inches (50 mm) or less in width.
 3. No measurement shall be made for concrete keys between adjoining beams or prestressed concrete planks.
 4. No measurement shall be made for fill concrete between the ends or adjoining prestressed concrete planks/box beams at bent caps or between the ends of prestressed concrete planks/box beams and abutment end walls.
 5. No measurement shall be made for inlet and junction box invert concrete.
 6. No measurement shall be made for any additional concrete required above the normal slab thickness for camber or crown.
- B. Plan Quantity. For those items measured for plan quantity payment, adequate calculations have been made. If no adjustment is required by Article 403S.12, additional measurements or calculations will not be required or made.
- C. Measured in Place. For those items not measured for Plan Quantity payment, measurement will be made in place, subject to the requirements of Article 403S.10.A.1 above.

403S.12 Payment

The work performed and materials furnished as prescribed by this item and measured in accordance with the applicable provisions of "Measurement" above will be paid for as follows.

The quantity to be paid for will be that quantity indicated in the contract documents and/or shown on the drawings, regardless of errors in calculations, except as may be modified by the following.

Plan Quantities will be adjusted:

- A. When a complete structure element has been erroneously included or omitted from the drawings, the quantity shown on the drawings for that element will be added to or deducted from the plan quantity and included for payment. A complete structure element will be the smallest portion of a total structure for which a quantity is included on the drawings. Quantities revised in this manner will not be subject to the provisions of the "General Conditions", Article 11.
- B. When the plan quantity for a complete structure element is in error by 5 percent or more, a recalculation will be made and the corrected quantity included for payment. Quantities revised in this manner will not be subject to the provisions of the "General Conditions", Article 11
- C. When quantities are revised by a change in design, the "plan quantity" will be increased or decreased by the amount involved in the design change. Quantities revised in this manner will be subject to the provisions of the "General Conditions", Article 11.

The party to the contract requesting the adjustment shall present to the other, a copy of the description and location, together with calculations of the quantity for the structure element involved. When this quantity is certified correct by the Engineer or designated representative, it will become the revised plan quantity.

Payment for increased or decreased costs due to a change in design on those items measured as "Cubic Yard", "Each", "Square Foot", "Square Yard" or "Linear Foot" will be determined by Change Order. Quantities revised in this manner will be subject to the provisions of the "General Conditions", Article 11.

The unit prices bid for the various classes of concrete shown shall include full compensation for furnishing, hauling, and mixing all concrete material; placing, finishing and curing all concrete; all grouting, pointing and finishing; furnishing and placing drains; furnishing and placing metal flashing strips; furnishing and placing expansion joint material required by this item; and for all forms and false work, labor, tools, equipment and incidentals necessary to complete the work.

- Pay Item No. 403S-CY:** (Structure or Structural Component) - Per Cubic Yard.
- Pay Item No. 403S-EA:** (Structure or Structural Component) - Per Each.
- Pay Item No. 403S-SY:** (Structure or Structural Component) - Per Square Yard.
- Pay Item No. 403S-LF:** (Structure or Structural Component) - Per Lineal Foot.

End

<i>SPECIFIC</i> CROSS REFERENCE MATERIALS
Standard Specification Item 403S, "Concrete For Structures"

City of Austin Standard Specification Items

<u>Designation</u>	<u>Description</u>
Item No. 401S	Structural Excavation and Backfill
Item No. 410S	Concrete Structures
Item No. 411S	Surface Finishes for Concrete

Texas Department of Transportation: Departmental Material Specifications

<u>Designation</u>	<u>Description</u>
DMS-4640	<u>Chemical Admixtures for Concrete</u>
DMS-4610	Fly Ash
DMS-4620	Ground Granulated Blast-Furnace Slag
DMS-4630	Silica Fume
DMS-4635	Metakaolin

American Association of State Highway & Transportation Officials, AASHTO Standard

Method of Test for

<u>Designation</u>	<u>Description</u>
Method T 26	Quality of Water to be Used in Concrete

American Concrete Institute, ACI

<u>Designation</u>	<u>Description</u>
ACI 211.1	Standard Practice for Selecting Proportions for Normal, Heavyweight, and Mass Concrete

American Society for Testing and Materials, ASTM

<u>Designation</u>	<u>Description</u>
ASTM C 94	Specification For Ready-Mixed Concrete
ASTM C 150	Specification For Portland Cement
ASTM C 685	Concrete Made By Volumetric Batching and Continuous Mixing

ASTM C-1260	Standard Test Method for Potential Alkali Reactivity of Aggregates
ASTM D-512	Test Methods for Chloride Ion in Water
ASTM D-516	Test Methods for Sulfate Ion in Water
ASTM D-4191	Test Method for Sodium in Water by Atomic Absorption
ASTM D-4192	Test Method for Potassium Water by Atomic Absorption
Texas Department of Transportation: <u>Manual of Testing Procedures</u>	
<u>Designation</u>	<u>Description</u>
TEX-203-F	Sand Equivalent Test
TEX-401-A	Sieve Analysis of Fine and Coarse Aggregate
TEX-406-A	Mineral Finer than 75 µm (No. 200) Sieve in Mineral Aggregates (Decantation Test for Concrete Aggregates)
TEX-408-A	Organic Impurities in Fine Aggregate for Concrete
TEX-410-A	Abrasion of Coarse Aggregate Using The Los Angeles Machine
TEX-411-A	Soundness of Aggregate by Use of Sodium Sulfate or Magnesium Sulfate
TEX-413-A	Determination of Deleterious Materials in Mineral Aggregate
TEX-415-A	Slump of Portland Cement Concrete
TEX-416-A	Air Content of Freshly-Mixed Concrete by the Pressure Method
TEX-418-A	Compressive Strength of Cylindrical Concrete Specimens
TEX-612-J	Acid Insoluble Residue

<i>SPECIFIC</i> CROSS REFERENCE MATERIALS (Continued)
Standard Specification Item 403S, "Concrete For Structures"

Texas Department of Transportation: Publications

<u>Designation</u>	<u>Description</u>
Bulletin C-11	Construction Bulletin

<i>RELATED</i> CROSS REFERENCE MATERIALS
Standard Specification Item 403S, "Concrete For Structures"

Texas Department of Transportation: Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges

<u>Designation</u>	<u>Description</u>
Item 360	Concrete Pavement
Item 420	Concrete Structures
Item 421	Hydraulic Cement Concrete
Item 427	Surface Finishes for Concrete
Item 431	Pneumatically Placed Concrete
Item 520	Weighing and Measuring Equipment

Texas Department of Transportation: Departmental Material Specifications

<u>Designation</u>	<u>Description</u>
DMS-4650	Hydraulic Cement Concrete Curing Materials and Evaporation Retardants"
DMS-6100	Epoxy and Adhesives
DMS 8900	Fly Ash

**Item No. 406S
Reinforcing Steel**

406S.1 Description

This item shall govern furnishing and placement of reinforcing steel, deformed and smooth, of the size and quantity indicated on the drawings and in accordance with these specifications.

This specification is applicable for projects or work involving either inch-pound or SI units. Within the text and accompanying tables, the inch-pound units are given preference followed by SI units shown within parentheses.

406S.2 Submittals

The submittal requirements of this specification item may include:

- A. Evidence that the steel reinforcement producer is included on the TxDOT list of approved producing mills
- B. Listing of the size, grade, type and quantity of reinforcing steel proposed for the project.
- C. If welding of reinforcing steel is proposed, evidence that carbon equivalent (C.E.) of the proposed steel is at least 0.55% with a report of chemical analysis showing the percentages of elements necessary to establish C.E.
- D. If epoxy coated steel is proposed, evidence that the steel reinforcement producer is included on the TxDOT list of approved epoxy coating applicators
- E. If epoxy coated steel is proposed, written certification that the epoxy-coated reinforcing steel meets the requirements of this Item with a copy of the manufacturer's control tests.
- F. When mechanical splices are proposed, the types of couplers proposed for use.

406S.3 Materials

A. Approved Mills

Prior to furnishing reinforcing steel, the producing mills must be included on the list of approved producing mills that is maintained by the Construction Division of the State of Texas Department of Transportation

B. Deformed Bars and Wire Reinforcement

Unless indicated otherwise on the drawings, Bar reinforcement shall be Grade 60 and deformed. Reinforcing steel must conform to one of the following:

ASTM A615/ 615M, Grades 40 or 60 (300 or 420)

ASTM A996/ 996M, Type A, Grades 40 or 60 (300 or 420)

ASTM A996/996M, Type R, Grade 60 (420), permitted in concrete pavement only (furnished as straight bars only without bends. Bend tests are not required)

ASTM A706/706M

In cases where the provisions of this item are in conflict with the provisions of the ASTM Designation to which reference is made, the provisions of this item shall govern.

The nominal size, area and weight (mass) of reinforcing steel bars covered by these specifications are as follows:

Bar Size Number 1/8 th ins (mm)	Nominal Diameter, inches (mm)	Nominal Area, Sq. ins. (mm ²)	Weight/Linear Foot Lbs. (kg)
2 (6)	0.250 (6.6)	0.05 (32)	0.167 (.075)
3 (10)	0.375 (9.5)	0.11 (71)	0.376 (.171)
4 (13)	0.500 (12.5)	0.20 (127)	0.668 (.303)
5 (16)	0.625 (15.5)	0.31 (198)	1.043 (.473)
6 (19)	0.750 (19.0)	0.44 (285)	1.502 (.681)
7 (22)	0.875 (22.0)	0.60 (388)	2.044 (.927)
8 (25)	1.000 (25.5)	0.79 (507)	2.670 (2.211)
9 (29)	1.128 (28.5)	1.00 (641)	3.400 (1.542)
10 (32)	1.270 (32.0)	1.27 (792)	4.303 (1.952)
11 (36)	1.410 (36.0)	1.56 (958)	5.313 (2.410)
14 (43)	1.693 (43.0)	2.25 (1552)	7.65 (3.470)
18 (57)	2.257 (57.5)	4.00 (2565)	13.60 (6.169)

Smooth, round bars shall be designated by size number through a No. 4. Smooth bars above No. 4 shall be designated by diameter in inches.

C. Smooth Bar and Spiral Reinforcement

Smooth bars and dowels for concrete pavement must have a minimum yield strength of 60 ksi (414 MPa) and meet ASTM A615/615M. Smooth bars that are greater in diameter than a No. 3 (10 mm) designation shall conform to ASTM A615 or meet the physical requirements of ASTM A36.

Spiral reinforcement shall be either smooth or deformed bars or wire of the minimum size or gauge indicated on the drawings. Bars for spiral reinforcement shall comply with ASTM A615 Grade 40(300), ASTM A996, Type A, Grade 40 (300); or ASTM A675, Grade 80(550), meeting dimensional requirements of ASTM A615. Smooth wire shall comply with ASTM A82, and deformed wire shall comply with ASTM A496.

D. Weldable Reinforcing Steel

Reinforcing steel to be welded must comply with ASTM A706 or have a carbon equivalent (C.E.) of at most 0.55%. A report of chemical analysis showing the percentages of elements necessary to establish C.E. is required for reinforcing steel that does not meet ASTM A706 to be structurally welded. No tack welding will be allowed. All welding shall conform to the requirements of AWS D1.1/D1.1M.

The requirements above do not apply to the following miscellaneous welding applications:

- Splicing reinforcing steel to extend bars in the bottom of a drilled shaft;
- Attaching chairs to the reinforcing steel cage of a drilled shaft;
- Armor joints and their supports;
- Screed rail and form hanger supports where permitted on steel units;
- Reinforcing steel to R-bars for lateral stability between prestressed beams, spirals, or bands of reinforcing bars in drilled shaft cages;
- Permanent bridge deck forms;
- Steel added in railing when slip-form construction is used; and

Other similar miscellaneous members that have no load carrying capacity in the completed structure.

E. Welded Wire Fabric

Wire shall conform to the requirements of the Standard Specifications for Cold-Drawn Steel Wire for Concrete Reinforcement, ASTM A 82 or A 496. Wire fabric, when used as reinforcement, shall conform to ASTM A 185 or A 497.

When wire is ordered by size numbers, the following relation between size number, diameter in inches and area shall apply unless otherwise indicated on the drawings:

Size, W Number 1/100 in ² (mm ²)	Nominal Diameter inch (mm)	Nominal Area, sq. inches (mm ²)
31 (200)	0.628 (16.0)	0.310 (200)
30 (194)	0.618 (15.7)	0.300 (194)
28 (181)	0.597 (15.2)	0.280 (181)
26 (168)	0.575 (14.6)	0.260 (168)
24 (155)	0.553 (14.0)	0.240 (155)
22 (142)	0.529 (13.4)	0.220 (142)
20 (129)	0.505 (12.8)	0.200 (129)
18 (116)	0.479 (12.2)	0.180 (116)
16 (103)	0.451 (11.5)	0.160 (103)
14 (90)	0.422 (10.7)	0.140 (90)
12 (77)	0.391 (9.9)	0.120 (77)
10 (65)	0.357 (9.1)	0.100 (65)
8 (52)	0.319 (8.1)	0.080 (52)
7 (45)	0.299 (7.6)	0.070 (45)
6 (39)	0.276 (7.0)	0.060 (39)
5.5 (35)	0.265 (6.7)	0.055 (35)
5 (32)	0.252 (6.4)	0.050 (32)
4.5 (29)	0.239 (6.1)	0.045 (29)
4 (26)	0.226 (5.7)	0.040 (26)
3.5 (23)	0.211 (5.4)	0.035 (23)
3 (19)	0.195 (5.0)	0.030 (19)
2.5 (16)	0.178 (4.5)	0.025 (16)
2 (13)	0.160 (4.1)	0.020 (13)
1.5 (9)	0.138 (3.5)	0.015 (9.7)
1.2 (8)	0.124 (3.1)	0.012 (7.7)
1 (6)	0.113 (2.9)	0.010 (6.5)
0.5 (3)	0.080 (2.0)	0.005 (3.2)

Where deformed wire is required, the size number shall be preceded by D and for smooth wire the prefix W shall be shown.

Welded wire fabric shall be designated as follows: 6 x 12 – W16 x W8, which indicates a 6 in. (150 mm) longitudinal wire spacing and 12-in (300 mm) transverse wire spacing with smooth No. 16 (103) wire longitudinally and smooth no. 8 (52) wire transversely.

F. Epoxy Coating

Epoxy coating shall be required as indicated on the drawings. Prior to furnishing epoxy-coated reinforcing steel, the epoxy applicator must be included on the list of approved applicators that is maintained by the Construction Division of the State of Texas Department of Transportation.

The reinforcing steel shall be epoxy coated in accordance with the following.

Epoxy Coating Requirements for Reinforcing Steel

Material	Specification
Bar	ASTM A775 or A934
Wire or Fabric	ASTM A884 Class A or B
Mechanical Coupler	As indicated on the drawings
Hardware	As indicated on the drawings

The epoxy coating material and coating repair material shall comply with TxDOT's DMS-8130, "Epoxy Powder Coating for Reinforcing Steel". The applicator shall not patch more than ¼ inch total length in any foot (20 mm total length in any meter) at the applicator's plant.

The epoxy-coated reinforcing steel shall be sampled and tested in accordance with TxDOT Test Method Tex-739-I, "Sampling and Testing Epoxy Coated Reinforcing Steel".

The identification of all reinforcing steel shall be maintained throughout the epoxy coating and fabrication and until delivery to the project site.

Written certification that the epoxy-coated reinforcing steel meets the requirements of this Item shall be provided along with a copy of the manufacturer's control tests.

G. Mechanical Couplers

When mechanical splices in reinforcing steel bars are indicated on the drawings, the following types of couplers may be used:

- Sleeve-filler
- Sleeve-threaded
- Sleeve-swaged, or
- Sleeve-wedge.

H. Chairs and Supports

Chairs and Supports shall be steel, precast mortar or concrete blocks cast in molds meeting the approval of the Engineer or designated representative of sufficient strength to position the reinforcement as indicated on the drawings when supporting the dead load of the reinforcement, the weight of the workers placing concrete and the weight of the concrete bearing on the steel. Chairs shall be plastic coated when indicated on the drawings.

Chair Types and Applicable Uses	
Structural or Architectural Elements (columns, beams, walls, slabs) exposed to weather, not subjected to sand blasting, water blasting or grinding.	Galvanized steel or steel chairs with plastic coated feet.
Structural or Architectural Elements exposed to weather and subject to sand blasting, water blasting or grinding.	Stainless steel chairs.
Structural or Architectural Elements not exposed to weather or corrosive conditions.	Uncoated steel chairs
Slabs and grade beams cast on grade.	Steel chairs with a base with 9 inch ² (58 cm ²) minimum area or sufficient area to prevent the chair from sinking into fill or subgrade. Precast mortar or concrete blocks meeting the requirements of this item may be used.

406S.4 Bending

The reinforcement shall be bent cold, true to the shapes indicated on the drawings. Bending shall preferably be done in the shop. Irregularities in bending shall be cause for rejection. Improperly fabricated, damaged or broken bars shall be replaced at no additional expense to the City. Damaged or broken bars embedded in a previous concrete placement shall be repaired using a method approved by the Engineer or designated representative.

Unless otherwise indicated on the drawings, the inside diameter of bar bends, in terms of the nominal bar diameter (d), shall be as follows:

Bends of 90 degrees and greater in stirrups, ties and other secondary bars that enclose another bar in the bend.

Bar Number in 1/8th inches (mm)	Diameter
3, 4, 5 (10, 13, 16)	4d
6, 7, 8	6d

All bends in main bars and in secondary bars not covered above.

Bar Number in 1/8th inches (mm)	Diameter
3 thru 8 (10 thru 25)	6d
9, 10, 11 (29, 32, 36)	8d
14, 18 (43, 57)	10d

406S.5 Tolerances

Fabricating tolerances for bars shall not be greater than shown on Standard (Detail) 406S-1.

406S.6 Storing

Steel reinforcement shall be stored above the surface of the ground upon platforms, skids or other supports and shall be protected as far as practicable from mechanical injury and surface deterioration caused by exposure to conditions producing rust. When placed in the work, reinforcement shall be free from dirt, paint, grease, oil or other foreign materials. Reinforcement shall be free from injurious defects such as cracks and laminations. Rust, surface seams, surface irregularities or mill scale will not be cause for rejection, provided the minimum dimensions, cross sectional area and tensile properties of a hand wire brushed specimen meets the physical requirements for the size and grade of steel indicated on the drawings.

406S.7 Splices

Splicing of bars, except when indicated on the drawings or specified herein, will not be permitted without written approval of the Engineer or designated representative. No substitution of bars will be allowed without the approval of the Engineer or designated representative. Any splicing of substituted bars shall conform to the requirements in the Table below.

Splices not indicated on the drawings will be permitted in slabs not more than 15 inches (380 mm) in thickness, columns, walls and parapets.

Splices will not be permitted in bars 30 feet (9.1 meters) or less in plan length unless otherwise approved. For bars exceeding 30 feet (9.1 meters) in plan length, the distance center to center of splices shall not be less than 30 feet (9.1 meters) minus 1 splice length, with no more than 1 individual bar length less than 10 feet (3 meters). Splices not indicated on the drawings, but permitted hereby, shall conform to the Table below. The specified concrete cover shall be maintained at such splices and the bars placed in contact and securely tied together.

Minimum Lap Requirements		
Bar Number in 1/8th inches (mm)	Uncoated Lap Length	Coated Lap Length
3 (10)	1 foot 4 inches (0.4 meters)	2 foot 0 inches (0.610 meters)
4 (13)	1 foot 9 inches (0.533 meters)	2 foot 8 inches (0.813 meters)
5 (16)	2 foot 2 inches (0.660 meters)	3 feet 3 inches (0.991 meters)
6 (19)	2 foot 7 inches (0.787 meters)	3 feet 11 inches (1.194 meters)
7 (22)	3 feet 5 inches (1.041 meters)	5 feet 2 inches (1.575 meters)
No. 8 (25)	4 feet 6 inches (1.372 meters)	6 feet 9 inches (2.057 meters)
No. 9 (29)	5 feet 8 inches (1.727 meters)	8 feet 6 inches (2.591 meters)
No. 10 (32)	7 feet 3 inches (2.210 meters)	10 feet 11 inches (3.327 meters)
No. 11 (36)	8 feet 11 inches (2.718 meters)	13 feet 5 inches (4.089 meters)

Spiral steel shall be lapped a minimum of 1 turn. Bar No. 14 and No. 18 may not be lapped.

Welded wire fabric shall be spliced using a lap length that includes an overlap of at least 2 cross wires plus 2 inches (50 mm) on each sheet or roll.

Splices using bars that develop equivalent strength and are lapped in accordance with the table above are permitted.

Welding of reinforcing bars may be used only where indicated on the drawings or as permitted herein. All welding operations, processes, equipment, materials, workmanship and inspection shall conform to the requirements indicated on the drawings. All splices shall be of such dimension and character as to develop the full strength of the bar being spliced.

End preparation for butt-welding reinforcing bars shall be done in the field, except Bar No. 6 and larger shall be done in the shop. Delivered bars shall be of sufficient length to permit this practice.

For box culvert extensions with less than 1 foot (0.3 meters) of fill, the existing longitudinal bars shall have a lap with the new bars as shown in the table above. For box culvert extensions with more than 1 foot (0.3 meters) of fill, a minimum lap of 12 inches (300 mm) will be required.

Unless otherwise indicated on the drawings, dowel bars transferring tensile stresses shall have a minimum embedment equal to the minimum lap requirements shown in the table above. Shear transfer dowels shall have a minimum embedment of 12 inches (300 mm).

406S.8 Placement

Reinforcement shall be placed as near as possible in the position indicated on the drawings. Unless otherwise indicated on the drawings, dimensions shown for reinforcement are to the centers of the bars. In the plane of the steel parallel to the nearest surface of concrete, bars shall not vary from plan placement by more than 1/12 of the spacing between bars. In the plane of the steel perpendicular to the nearest surface of concrete, bars shall not vary from plan placement by more than 1/4 inch (6 mm). Cover of concrete to the nearest surface of steel shall be as follows:

	Minimum Cover, Inches (mm)
(a) Concrete cast against and permanently exposed to earth	3 (76 mm)
(b) Concrete exposed to earth or weather:	
Bar No. 6 (19) through No. 18 bars (57)	2 (51 mm)
Bar No. 5 (16), W31 (W200) or D31 (D200) wire and smaller	1 ½ (38 mm)
(c) Concrete not exposed to weather or in contact with ground:	
Slabs, walls, joists:	
Bar No. 14 (43) and 18 (57)	1 ½ (38mm)
Bar No. 11 (36) and smaller	1 (25 mm)
Beams, columns:	
Primary reinforcement, ties, stirrups, spirals	1 ½ (38 mm)
Shells, folded plate members:	
Bar No. 6 (19) and larger	1 (25 mm)
Bar No. 5 (16), W31 (W200) or D31 (D200) wire, and smaller	1 (25 mm)

Vertical stirrups shall always pass around the main tension members and be attached securely thereto.

The reinforcing steel shall be located accurately in the forms and held firmly in place before and during concrete placement by means of bar supports that are adequate in strength and number to prevent displacement and to keep the steel at the required distance from the form surface. Bars shall be supported by means of approved galvanized metal spacers, metal spacers with plastic coated tips, stainless steel spacers, plastic spacers or approved precast mortar or concrete blocks when supports are in contact with removable or stay-in-place forms. Bright basic bar supports shall be used to support reinforcing steel placed in slab overlays on concrete panels or on existing concrete slabs. Bar supports in contact with soil or subgrade shall be approved.

For bar supports with plastic tips, the plastic protection must be at least 3/32 in. (2.4 mm) thick and extend upward on the wire to a point at least 1/2 in. (12.5 mm) above the formwork.

For approval of plastic spacers on a project, representative samples of the plastic shall show no visible indications of deterioration after immersion in a 5 percent solution of sodium hydroxide for 120 hours.

All accessories such as tie wires, bar chairs, supports, or clips used with epoxy-coated reinforcement shall be of steel, fully coated with epoxy or plastic. When approved by the Engineer or designated representative, plastic supports may also be used with epoxy-coated reinforcement.

All reinforcing steel shall be tied at all intersections, except that where spacing is less than 1 foot (300 mm) in each direction, alternate intersections only need be tied. For reinforcing steel cages for other structural members, the steel shall be tied at enough intersections to provide a rigid cage of steel. Mats of wire fabric shall overlap each other 1 full space as a minimum to maintain a uniform strength and shall be tied at the ends and edges.

Where prefabricated deformed wire mats are specified or if the Contractor requests, welded wire fabric may be substituted for a comparable area of steel reinforcing bar plan, subject to the approval of the Engineer or designated representative.

Mortar or concrete blocks shall be cast to uniform dimensions with adequate bearing area. A suitable tie wire shall be provided in each block, to be used for anchoring to the steel. Except in unusual cases and when specifically authorized by the Engineer, the size of the surface to be placed adjacent to the forms shall not exceed 2 1/2 inches (63.5 mm) square or the equivalent thereof in cases where circular or rectangular areas are provided. Blocks shall be cast accurately to the thickness required and the surface to be placed adjacent to the forms shall be a true plane, free of surface imperfections. The blocks shall be cured by covering them with wet burlap or mats for a period of 72 hours. Mortar for blocks should contain approximately 1 part hydraulic cement to three parts sand. Concrete for blocks should contain 850 pounds of hydraulic cement per cubic yard (500 kilograms per cubic meter) of concrete.

Individual bar supports shall be placed in rows at 4-ft (1.22 meters) maximum spacing in each direction. Continuous type bar supports shall be placed at 4-ft (1.22 meters) maximum spacing. Continuous bar supports shall be used with permanent metal deck forms.

The exposure of the ends of longitudinals, stirrups and spacers used to position the reinforcement in concrete pipe and in precast box culverts or storm drains is not a cause for rejection.

Reinforcing steel for bridge slabs, top slabs of direct traffic culverts, and top slabs of prestressed box beams at all intersections, except tie only alternate intersections where spacing is less than 1 ft. (300 mm) in each direction.

For steel reinforcing cages for other structural members, reinforcement shall be supported and tied in such a manner that a sufficiently rigid cage of steel is provided. Fasten mats of wire fabric securely at the ends and edges. If the cage is not adequately supported to resist settlement or floating upward of the steel, overturning of truss bars or movement in any direction during concrete placement, permission to continue concrete placement will be withheld until corrective measures are taken. Sufficient measurements shall be made during concrete placement to insure compliance with the above.

No concrete shall be deposited until the Engineer or designated representative has reviewed the placement of the reinforcing steel and all mortar, mud, dirt, etc, shall be cleaned from the reinforcement, forms, workers' boots and tools. Do not place concrete until authorized by the Engineer or designated representative

406S.9 Handling, Placement and Repair of Epoxy-coated Reinforcement Steel

A. Handling

Systems for handling coated-reinforcement with padded contact areas shall be provided. Handling bands shall be padded to prevent damage to the coating. Bundles of coated reinforcement shall be lifted with a strongback, spreader bar, multiple supports or a platform bridge. The bundled reinforcement shall be carefully transported and stored on protective cribbing. The coated reinforcement should not be dropped or drug during handling.

B. Construction Methods

Coated reinforcement shall not be flame-cut but shall be sawn or shear-cut only when approved. Cut ends shall be coated as specified in Section C, "Repair of Coating".

Coated reinforcement steel shall not be welded or mechanically coupled except where specifically indicated on the drawings. When welding or coupling is indicated on the drawing, the epoxy coating shall be removed at least 6 in. (150 mm) beyond the weld limits before welding and 2 in. (50 mm) beyond the limits of the mechanical coupler before assembly. After the welding or coupling operation is completed the steel shall be cleaned of oil, grease, moisture, dirt, welding contamination (slag or acid residue) and rust to a near-white finish. The existing epoxy coating shall be examined for damage and any damaged or loose epoxy shall be removed to expose sound epoxy coating.

After cleaning the coated-steel, the splice area shall be coated with epoxy repair material to a thickness of 7 to 17 mils (0.18 to 0.43 mm) after curing. A second application of the repair material shall be applied to the bar and coupler interface to ensure complete sealing of the joint.

C. Repair of Coating

The material used for coating repair shall comply with the requirements of this Item and ASTM D3963/D3963M, "Specification for Fabrication and Jobsite Handling of Epoxy-coated Reinforcing Steel Bars". Repairs shall be made in accordance with procedures recommended by the manufacturer of the epoxy coating powder. For areas to be patched, a minimum coating thickness as required for the original coating shall be applied. All visible damage to the coating shall be repaired.

Sawed and sheared ends, cuts, breaks and other damage shall be promptly repaired before additional oxidation occurs. The areas to be repaired shall be cleaned to ensure that they free from surface contaminants. Repairs shall be made in the shop or in the field as required.

406S.10 Measurement

The measurement of quantities of reinforcement furnished and placed will be based on the calculated weight of the steel actually placed as indicated on the drawings, with no allowance made for added bar lengths for splices requested by the Contractor nor for extra steel used when bars larger than those indicated on the drawings are used or for a higher grade of steel that is substituted with the permission of the Engineer or designated representative. Tie wires and supporting devices will not be included in the calculated weights. The calculated weight of bar reinforcement will be determined using the theoretical bar weight set forth in this item.

Measurement required by a change in design will be computed as described above for the actual steel required to complete the work.

406S.11 Payment

Reinforcing steel will generally not be paid for directly, but shall be included in the unit price bid for the items of construction in which the reinforcing steel is used.

When specified in the contract bid form as a separate pay item, this item shall be paid for at the contract unit price bid per pound of "Reinforcing Steel". The unit bid price shall include full compensation for all work specified herein including furnishing, bending, fabricating, welding and placing reinforcement, for all clips, blocks, metal spacers, ties, chairs, wire or other materials used for fastening reinforcement in place and for all tools, labor, equipment and incidentals necessary to complete the work.

Payment, when included as a contract pay item, will be made under:

- Pay Item No. 406S-RC:** Reinforcing Steel - Per Pound.
- Pay Item No. 406S-ERC:** Epoxy-Coated Reinforcing Steel - Per Pound.

END

SPECIFIC CROSS REFERENCE MATERIALS
Standard Specification Item 406S, "Reinforcing Steel"

American Society for Testing and Materials, ASTM	
Designation	Description
ASTM A 36/A 36M	Carbon Structural Steel
ASTM A 82	Steel Wire, Plain, for Concrete Reinforcement
ASTM A 185	Steel Welded Wire Fabric, Plain, for Concrete Reinforcement
ASTM A 496	Steel Wire, Deformed, for Concrete Reinforcement
ASTM A 497	Steel Welded Wire Fabric, Deformed, for Concrete Reinforcement
ASTM A 615/A 615M	Deformed and Plain Billet-steel Bars for Concrete Reinforcement
ASTM A 675/A 675M	Steel Bars, Carbon, Hot-Wrought, Special Quality, Mechanical Properties
ASTM A 706/A 706M	Low- Alloy Steel Deformed and Plain Bars for Concrete Reinforcement
ASTM A 775/A 775M	Epoxy-Coated Reinforcing Steel Bars
ASTM A 884/A 884M	Epoxy-Coated Steel Wire and Welded Wire Fabric For Reinforcement
ASTM A 934/A 934M	Epoxy-Coated Prefabricated Reinforcing Steel Bars

ASTM A 996/A 996M Rail-Steel and Axle-Steel Deformed Bars for Concrete Reinforcement
 ASTM D3963/D3963M Fabrication and Jobsite Handling of Epoxy-coated Reinforcing Steel Bars

Texas Department of Transportation: Manual of Testing Procedures

Designation	Description
Tex-739-I	Sampling and Testing Epoxy Coated Reinforcing Steel

City of Austin Standard (Details)

Designation	Description
Standard 406S-1	Reinforced Steel Tolerances

Texas Department of Transportation: Departmental Material Specifications

Designation	Description
DMS 8130	Epoxy Powder Coating for Reinforcing Steel

American Welding Society

Designation	Description
AWS D1.1/D1.1M	Structural Welding Code

RELATED CROSS REFERENCE MATERIALS
Standard Specification Item 406S, "Reinforcing Steel"

City of Austin Standard Specification Items

Designation	Description
Item No. 360	Concrete Pavement
Item No. 403S	Concrete for Structures
Item No. 410S	Concrete Structures
Item No. 414S	Concrete Retaining Walls
Item No. 420S	Drilled Shaft Foundations
Item No. 830S	Traffic Signal Controller Foundation
Item No. 831S	Traffic Signal Drilled Shaft Foundation

Texas Department of Transportation: Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges

Designation	Description
Item No. 360	Concrete Pavement
Item No. 420	Concrete Structures
Item No. 421	Hydraulic Cement Concrete
Item No. 422	Reinforced Concrete Slab
Item No. 423	Retaining Walls
Item No. 440	Reinforcing Steel